

MATERIALS AND METHODS

Preparation of glucose-displayed surfaces Unless otherwise stated, the conventional plastic surface in an 8-well culture plate (surface area: 8.6 cm², Nalge Nunc, Roskilde, Denmark) was used as a starter material for displaying glucose. To create a template with hydroxyl group on the surface, an aqueous solution of 50 μmol/cm³ potassium *tert*-butoxide was poured into each well, and then the well was incubated for 1 h under an ambient condition, followed by irrigating three times with sterilized water. An aqueous solution of 360 μmol/cm³ glutaraldehyde was introduced into the well which was then allowed to stand for 1 h and washed thoroughly with sterilized water. The well was treated with 360 μmol/cm³ tris(2-aminoethyl) amine solution (adjusted to pH 9.0 with 1 mol/cm³ NaOH) for 1 h and rinsed with sterilized water.

To display glucose as a ligand on the template surface, D- and/or L-glucose solution (totally 0.1 μg/cm³) was added to and left in each well for 2 h. The ratio of D- to L-glucose in the applied solution was changed so as to obtain the surface preparations with 0, 25, 50, 75 and 100% D-glucose display. A 0.5 μmol/cm³ sodium borohydride solution was poured into the well, and after standing for 24 h, the well was washed twice with phosphate buffered saline (PBS, Sigma-Aldrich, St. Louise, MO, USA) prior to cell seeding.

When a 25-cm² T-flask (Nunclon Delta Flask; Nalge Nunc) was used, the procedures for displaying glucose on the surface were almost the same as describe above.

1 **Cell cultures** Human mammary epithelial cells (hTERT-HME1; Clontec
2 Laboratories, San Diego, CA, USA) were obtained in a frozen state, and then the cells
3 in vials were thawed according to the supplier's instruction. These cells were
4 subcultured in a 25-cm² T-flask at 37 °C under a 5% CO₂ atmosphere using
5 HuMedia-KG2 serum-free medium with 6.0 μmol/cm³ D-glucose (Kurabo Ind., Osaka).
6 For the experiments, the initial concentration of viable cells, determined by trypan blue
7 exclusion, was fixed at $X_0 = 5.0 \times 10^3$ cells/cm², and the cultures were conducted on the
8 prepared culture surfaces using the medium with or without insulin (10 μg/cm³ when
9 added) under the same conditions as described above.

10 For tracing dynamic variation in cell morphology, time-lapse observation of
11 individual cells was conducted, and the images captured through a CCD camera system
12 were processed according to the previous papers which described details of tools (29,
13 30). The value of roundness, R_c , of each cell was determined by the following equation,
14 employing the projected area and periphery, respectively a_c and l_c of a single cell, which
15 were obtained by extracting the cellular edge using a line-drawing tool (WinROOF,
16 Mitani Co., Fukui).

$$17 \quad R_c = \frac{2(\pi a_c)^{1/2}}{l_c} \quad ; \quad 0 < R_c \leq 1 \quad (1)$$

18 To evaluate cell attachment and apparent cell morphology at 24 h after seeding,
19 the triplicate wells were picked up, and the bottom surface images were captured at five
20 different positions in each well by using a CCD camera (CS6931; Toshiba Teli, Tokyo)
21 attached to a microscope (area of captured image: 2.4 mm²). The efficiency of cell
22 attachment, X_{24}/X_0 , defined as a ratio of attached cells at 24 h against seeded cells on

1 five images, was determined in each well. The overall roundness, R_{oc} of cells in each
2 well was calculated by the following equation.

$$3 \quad R_{oc} = \frac{2(\pi A_{oc})^{1/2}}{L_{oc}}; \quad 0 < R_{oc} \leq 1 \quad (2)$$

4 Here, the overall area and periphery, respectively A_{oc} and L_{oc} , of all cells projected
5 on five images in each well were employed.

6 The values of X_{24}/X_0 and R_{oc} were recorded as means, represented by \bar{X}_{24} / \bar{X}_0
7 and \bar{R}_{oc} respectively, from the measurements for triplicate wells.

8 **Treatments of cells for blocking GLUTs and integrin** For antibody
9 treatments, the cells were recovered from the subculturing flasks by trypsin digestion,
10 and were in advance incubated with 0.5% Block Ace (Dainippon Sumitomo Pharma Co.,
11 Ltd., Osaka) for 30 min at 37°C for masking nonspecific binding sites on the cells. The
12 resultant cells were resuspended at 6.4×10^6 cells/cm³ in HuMedia-KG2 medium
13 containing 0.5% Block Ace. A polyclonal antibody against GLUT1 (1:100 dilution,
14 Alpha Diagnostic International Inc., San Antonio, TX, USA), and monoclonal
15 antibodies against GLUT4 (1:200 dilution, Biogenesis, Poole, UK) and integrin $\alpha_5\beta_1$
16 (1:50 dilution, Chemicon International, Inc. Temecula, USA) were adequately blended
17 with the medium, and the cells were treated with the respective antibodies for 1 h at 4°C
18 with gentle mixing every 20 min. The antibody-treated or non-treated cells were
19 cultured on the indicated surfaces to examine the cell attachment and morphology.

20 **Fluorescent microscopy for cytoskeletal observation and GLUT localization**

21 For visualization of the cytoskeletal elements and GLUTs, the cells were washed three
22 times with PBS and fixed with 4% paraformaldehyde in PBS for 10 min at room

1 temperature. They were then rinsed with PBS and permeabilized by incubating for 3
2 min in 0.1% Triton X-100. After washing again with PBS, nonspecific binding sites on
3 the cells were masked with Block Ace by incubating for 1 h at room temperature. The
4 cells were then treated with anti-GLUT1, anti-GLUT4 and/or anti-vinculin primary
5 antibodies (Sigma-Aldrich) that were adequately diluted in PBS containing 10% Block
6 Ace. After washing with PBS and rinsing with Tris-buffed saline (DakoCytomation
7 Carpinteria, CA, USA), the cells were subjected to immunolabeling with Alexa Fluor
8 568 goat anti-mouse IgG (Molecular Probes, Eugene, OR, USA). For the
9 immunolocalization of F-actin, the cells were washed with PBS and then stained with
10 Alexa Fluor 488 phalloidin (Molecular Probes). The treated cells were washed three
11 times with PBS and then mounted on a sample slide with Prolong Antifade solution
12 (Molecular Probes). Fluorescent images were acquired using a confocal laser scanning
13 microscope (Model FV-300, Olympus, Osaka). For stereoscopic observation of cells, a
14 series of images was piled up longitudinally at a 0.2 μm interval.

15 RESULTS

16 **Cellular behaviours on glucose-displayed surfaces** To examine the
17 interaction between epithelial cells and glucose molecules displayed on the surface, the
18 cultures were performed with the insulin administration at 24 h of culture time. Figure 1
19 shows the changes in R_c values of representative cells in the courses of cultures on the 0,
20 50 and 100% D-glucose-displayed surfaces. After seeding in the insulin-free medium,
21 the cells on 50% D-glucose-displayed surface started to adhere and maintained a
22 stretched shape with $R_c = 0.66\text{--}0.78$ (Fig. 1B) while the R_c values on both 0 and 100%

FIG. 1

1 D-glucose-displayed surfaces were 0.92–0.99 and 0.90–0.99, respectively (Fig. 1A and
2 C). After the insulin administration, on 100% D-glucose displayed surface, the cell
3 immediately elongated and reached $R_c = 0.70$ at $t = 60$ min (Fig. 1C), while the cells on
4 50% D-glucose-displayed surface exhibited round shape with $R_c = 0.89$ at $t = 60$ min
5 (Fig. 1B). These results mean that the different morphological changes occurred,
6 accompanied with the extension and contraction of the cells after the insulin
7 administration on 50 and 100% D-glucose-displayed surfaces. These morphological
8 differences between the cells on the three surfaces are also obvious on typically selected
9 snapshots presented at the upper side of Fig. 1. Thus the time-lapse observation revealed
10 that the cells made the distinct response to the insulin administration when cultured on
11 the surfaces with different ratios of D-glucose display.

12 To examine in detail the cell behaviors on the glucose-displayed surfaces, the
13 cultures were conducted for 24 h in the presence or absence of insulin on the surfaces
14 with various ratios of D-glucose display. As shown in Fig. 2A, there was no significant
15 difference in the \bar{X}_{24} / \bar{X}_0 values on the glucose-displayed surfaces, showing the same
16 levels in efficiency of cell attachment whether insulin existed or not.

17 The morphological examination was also conducted at 24 h after seeding in terms
18 of the \bar{R}_{oc} value (Fig. 2B). In the presence of insulin, the \bar{R}_{oc} value decreased with
19 increasing ratio of D-glucose displayed on the surfaces, being $\bar{R}_{oc} = 0.88$ and 0.76 at 0
20 and 100% D-glucose display, respectively. In the insulin-free culture, on the other hand,
21 a concave profile of \bar{R}_{oc} value was obtained and the value on 100%
22 D-glucose-displayed surface was $\bar{R}_{oc} = 0.87$, the value of which was comparable to
23 that on 0% D-glucose-displayed surface. On 50% D-glucose-displayed surface, the value

FIG. 2

1 of \bar{R}_{oc} was minimized to be 0.77 which was 13% reduction, as compared to that on the
2 surface without D-glucose display.

3 **Blocking effects of GLUTs and integrin** For further understanding the
4 mechanism of cell attachment, the cells were in advance treated with antibodies for
5 GLUTs1 and/or 4, and then were subjected to seeding on the glucose-displayed
6 surfaces. As shown in Fig. 3, no significant difference in the efficiency of cell
7 attachment was recognized on the D-glucose-displayed surfaces, giving \bar{X}_{24} / \bar{X}_0 value
8 of nearly unity whether insulin existed or not. In a similar way, the cell attachment test
9 was conducted using cells treated with the antibody for integrin $\alpha_5\beta_1$ on the
10 D-glucose-displayed surfaces. The blocking of integrin $\alpha_5\beta_1$ caused significant reduction
11 of cell attachment, resulting in $\bar{X}_{24} / \bar{X}_0 = 0.61$ on 0% D-glucose-displayed surface in
12 the presence of insulin. In addition, the \bar{X}_{24} / \bar{X}_0 values on the D-glucose-displayed
13 surfaces in the presence of insulin slightly increased on 100% D-glucose ($\bar{X}_{24} / \bar{X}_0 =$
14 0.78), compared to that on 0% D-glucose-displayed surface (Fig. 3). These results can
15 support the view that cell attachment mainly depends on the integrin mediation on the
16 glucose-displayed surfaces examined in this work.

FIG. 3

17 The test of morphological change was also conducted by culturing the cells with
18 the GLUT blockings for 24 h. As shown in Fig. 4, in the insulin-free cultures on the
19 D-glucose-displayed surfaces, the values of \bar{R}_{oc} for the single blocking of GLUT1 and
20 double blocking of GLUTs1 and 4 were kept to be levels over $\bar{R}_{oc} = 0.87$, meaning no
21 notable morphological variation due to inhibition of cell stretching. However, in the
22 culture of the cells with single blocking of GLUT4, the \bar{R}_{oc} profile on various

FIG. 4

1 D-glucose-displayed surfaces was overlapped with that in the culture of the cells with
2 non-blocking of GLUTs. In the insulin-containing culture, the single blocking of
3 GLUTs1 or 4 caused the concave profile of \bar{R}_{oc} value against the ratios of D-glucose
4 displayed on the surfaces, and the minimum \bar{R}_{oc} values of $\bar{R}_{oc} = 0.77$ and 0.78 were
5 obtained on 50 and 75% D-glucose displayed surfaces, respectively. When the cells
6 experienced the double blocking of GLUTs1 and 4, the stretching of cells was not
7 appreciable in the presence of insulin, being no significant variation in \bar{R}_{oc} value, in
8 analogy to that in the insulin-free culture. These results indicated that the mediation
9 between D-glucose and GLUTs participates not only in the cell attachment to surface but
10 also in the morphological change. The concave profile of \bar{R}_{oc} value was considered to
11 attribute to the quantitative balance between D-glucose displayed on the surface and
12 GLUTs expressed on the cellular membrane.

13 **Cytoskeletal formation and GLUT localization** To confirm the cytoskeletal
14 formation associated with integrin- and GLUT-mediated bindings, the fluorescent
15 microscopy was applied for the cells cultured for 24 h on the D-glucose-displayed
16 surfaces in the presence and absence of insulin. As shown in Fig. 5, distinct fibers of
17 F-actin with vinculin spots were recognized under all the examined conditions.
18 Especially, the vinculin spots at an inner part of cell on 100% D-glucose-displayed
19 surface clearly appeared with transversal stress fibers of F-actin, meaning the promoted
20 formation of focal contacts not only at a periphery but also at a whole body of cell in the
21 presence of insulin.

22 As shown in Fig. 6, GLUT1 was expressed under all the conditions, especially at
23 inner parts of a cell body where filopodia and lamellipodia of F-actin did not exist, while

FIG. 5

FIG. 6

1 the cells on 100% D-glucose-displayed surface in the presence of insulin exhibited
2 nebulous distribution of GLUT1 expression at a whole cell body including the top of
3 filopodia. In contrast with GLUT1 localization in the cells, a notable difference was
4 seen in the distribution of GLUT4 in association with the stimulation of the cells by
5 insulin. As demonstrated in Fig 6, GLUT4 spots were observed around the nucleus
6 under the insulin-free condition, and the spatial distribution of GLUT4 was seldom
7 observed on the basal side of cell. In the presence of insulin, the exhibition of GLUT4
8 on the cytoplasmic membrane was observed. On 100% D-glucose-displayed surface,
9 punctuate GLUT4 spots were widely scattered on the basal and apical sides of cell,
10 whereas the cell on 0% D-glucose-displayed surface showed intensive GLUT4 spots
11 only on the apical side. These findings suggest that the insulin stimulation facilitates,
12 together with D-glucose display, the localization of GLUTs1 and 4 to cellular parts near
13 the cell edges.

14 DISCUSSION

15 **Integrin and GLUTs mediate cell attachment and spreading on**
16 **D-glucose-displayed surface** A series of cellular behaviors including adhesion,
17 migration, division and differentiation occurs during *in vitro* culture of
18 anchorage-dependent cells. Especially, the cell attachment onto a surface and
19 subsequent morphological change are important events until growth initiation after
20 seeding. In this study, we examined the mechanism concerning the morphological
21 response of epithelial cells to glucose molecules displayed on the surface under the
22 culture conditions with and without insulin. Integrins are crucial transmembrane

1 proteins for cell-ECM bindings and initial cell attachment generally relies on the
2 integrin-mediation (1, 5, 7). The blocking experiments for integrin $\alpha_5\beta_1$ binding
3 indicated that the integrin mechanism mainly contributed to cell attachment rather than
4 GLUT-mediated bindings (Fig. 3), which supported the consideration that the latter
5 bindings made primary contribution to the morphological change of epithelial cells.

6 In mammalian cells, the facilitative uptake of D-glucose is mediated by a family
7 of specialized GLUTs. According to current reports (26, 27), there are at least 13
8 isoforms of facultative GLUTs that are differentially expressed in various cell species.
9 Cellular uptake of D-glucose can be performed by expressing GLUTs on cell surface
10 through a series of events such as synthesis of GLUTs in cytoplasm, translocation of
11 vesicle-associated GLUTs to cytoplasmic membrane and fusion of GLUT vesicles with
12 cytoplasmic membrane. In addition, GLUTs show the sharp specificity of binding
13 affinity against glucose isomers, that is, the affinity of GLUTs is high against D-glucose,
14 while being extremely low against L-glucose. D-Glucose itself is contingent to be an inert
15 component to induce cell signaling. But it is most likely that such the high affinity can
16 work as the cell anchoring mechanism via GLUT mediation for D-glucose molecules
17 displayed on the surface. In the case of insulin-sensitive cells such as adipose cells,
18 about 50% of intracellular GLUT4 is translocated onto the cytoplasmic membrane when
19 activated by insulin, providing a 10-fold increase in the amount of the transporter on
20 cell surface (28). The overall insulin-dependent shifts in the cellular dynamics of GLUT
21 vesicle trafficking result in an increase of GLUT4 on the cell surface, while GLUT1 is
22 localized both to the cytoplasmic membrane and intracellular storage sites (26-28, 31).
23 These natures of GLUTs1 and 4 seem to be concordant with our results obtained in the

1 culture of epithelial cells on the D-glucose-displayed surfaces in the absence and
2 presence of insulin. Insulin stimulation caused rapid change in cell morphology within
3 40 min on 100% D-glucose-displayed surface, possibly owing to display of GLUT4 on
4 the cytoplasmic membrane (Fig. 1), and the immunofluorescence staining clarified the
5 translocation of GLUT4 (Fig. 6). Furthermore, stainings of GLUTs and F-actin showed
6 the co-localization of GLUTs on the leading edges of cells with filopodia and
7 lamellipodia when cultured on 100% D-glucose-displayed surface with insulin, though
8 GLUTs were observed exclusively in the cell body on 0% D-glucose-displayed surface.
9 Especially, GLUT4 was observed in the cytoplasmic membrane on the apical side of
10 cells when cultured on 0% D-glucose-displayed surface in the presence of insulin.

11 **Morphological variation depends on quantitative balance of GLUTs and**
12 **D-glucose displayed** In the present work, the drastic variation in cell morphology
13 was also induced by changing the ratio of D-glucose displayed on the surface (Fig. 2).
14 The morphological variation was recognized in culture of rabbit chondrocytes by
15 changing the density of D-glucose displayed on surface (29). This morphological
16 variation can be explained according to the “receptor saturation” model proposed by
17 Gaudet *et al.* (32). They reported morphological variation of fibroblast cells cultured on
18 a fibronectin-coated surface where cellular integrin and fibronectin function as receptor
19 and binding sites, respectively. The model states that the morphological variation occurs
20 owing to the quantitative balance between binding sites on surface and receptor sites on
21 the cytoplasmic membrane as follows. Much lower density of binding sites, as
22 compared with receptor sites, leads to a round shape of cells, associated with weak cell
23 attachment on the surface. With an increase in density of binding sites, cell morphology

1 transfers to a stretched shape. Further increment in density of binding sites yields round
2 shaped cells with strong cell attachment on the surface. Ultimately an appropriate
3 balance between binding and receptor sites makes the cells stretched.

4 Based on the data obtained in our experiments, D-glucose molecules and GLUTs
5 are considered to work as binding and receptor sites, respectively, as illustrated in Fig. 7.

6 In the absence of insulin, the cells on 0% D-glucose-displayed surface became relatively
7 round shape, likewise in the case of cells cultured on the plain surface in a conventional
8 culture well (33, 34), owing to no binding sites for GLUT mediation. With an increase
9 in the ratio of D-glucose on the surface (see Arrow A in Fig. 7), the cells showed
10 excessive stretching; while cell stretching on 100% D-glucose-displayed surface was
11 inhibited owing to shortage of GLUTs, resulting in the concave profile of \bar{R}_{oc} value
12 (Fig. 2). In the absence of insulin, however, blocking of GLUT1 caused the hindrance of
13 stretching at any ratio of D-glucose displayed on the surface, while the profile of \bar{R}_{oc}
14 value with blocking of GLUT4 resembled the profile without blocking (Fig. 4). These
15 facts suggest that the morphological variation in the absence of insulin was caused by
16 fluctuation in GLUT1 expression. In the presence of insulin, with an increase in the
17 ratio of D-glucose displayed on the surface, the cell stretching was promoted, and on
18 100% D-glucose-displayed surface, the stretching was the most remarkable. These facts
19 mean that the insulin-encouraging expression of GLUT4 on the cytoplasmic membrane
20 as receptor sites could maintain the stretch shape (see Arrow B in Fig. 7), even through
21 the hindrance of stretching in the absence of insulin occurred owing to reduction of
22 GLUT4 expression as receptor sites. A reduction in receptor sites was also achieved by
23 the GLUT blocking experiment in the present work (see Arrow C in Fig. 7). The single

1 blocking of GLUTs1 or 4 caused the hindrance of stretching on 100% D-glucose
2 displayed surface, again resulting in the concave profile of \bar{R}_{oc} value (Fig. 4). The
3 double blockings of GLUTs1 and 4 led to fewer receptor sites, being attributed to the
4 hindrance of stretching at any ratio of D-glucose displayed on the surface. These results
5 support the view that the receptor saturation model can be valid for the GLUT
6 mediation mechanism.

7 According to Cox *et al.*, a biphasic relationship existed between density of coated
8 fibronectin and activation of Rho family of GTPases in terms of regulating the
9 spreading and motility of fibroblasts (35). This trend was concordant with our results
10 obtained in the culture of epithelial cells on 100% D-glucose-displayed surface in the
11 presence of insulin. On 100% D-glucose-displayed surface the cells exhibited increased
12 formation of focal contacts, with the developments of distinct vinculin spots, suggesting
13 that the grasping GLUTs on the cytoplasmic membrane with D-glucose on the surface
14 caused the active formation of the contacts (Fig. 6). It is considered that D-glucose
15 display on the surface permits the cells to be in close contact with the surface through
16 grasping of GLUTs on the cytoplasmic membrane, which is attributable to the
17 promotion of focal contact formation.

18 The present work proposed the possible mechanism of cell anchoring and
19 morphological change in the culture of human epithelial cells on the D-glucose
20 displayed surface. The variation in the ratio of D-glucose displayed caused the cellular
21 morphological change which depended on the culture condition with or without insulin.
22 The cultures of cells with blockings for GLUTs1 and 4 as well as integrin $\alpha_5\beta_1$ revealed
23 that cell attachment and morphology were dominantly governed by the mediations via

1 integrin and GLUTs, respectively. In addition, the fluorescence microscopy for F-actin,
2 vinculin, and GLUTs clarified the localization of integrin-mediated as well as
3 GLUT-mediated anchoring, inducing the consideration that the morphological change of
4 cells is responsible for the variation in the quantitative balance between D-glucose
5 density on culture surface and GLUTs on the cytoplasm membrane, associated with the
6 promoted formation of focal contacts by GLUT mediation. It is expected that the
7 GLUT-mediated anchoring will offer a synergistic impact on the cell signaling by means
8 of co-immobilization of D-glucose and stimulator molecules targeting receptors on the
9 cell membrane.

10

ACKNOWLEDGEMENTS

11 The present study was conducted as parts of the programs “Center for integrated
12 cell and tissue regulation” for the Center of Excellent (21st COE), and
13 “Multidisciplinary research laboratory system” organized in the Graduate School of
14 Engineering Science, Osaka University. This work also received financial supports in
15 part by a Grant-in-Aid for Scientific Research (No. 17360398) from the Ministry of
16 Education, Culture, Sports, Science and Technology and by a grant for Research on
17 Human Genome, Tissue Engineering and Food Biotechnology from the Ministry of
18 Health, Labour, and Welfare, Japan.

REFERENCES

- 1
2 1. **Geiger, B., Bershadsky, A., Pankov, R., and Yamada, K. M.:** Transmembrane
3 extracellular matrix-cytoskeleton crosstalk. *Nat. Rev. Mol. Cell Biol.*, **2**, 793–805
4 (2001).
- 5 2. **DeMali, K. A., Wennerberg, K., and Burridge, K.:** Integrin signaling to the actin
6 cytoskeleton. *Curr. Opin. Cell Biol.*, **15**, 572–582 (2003).
- 7 3. **Bernhard, W. H. and Beat, A. I.:** Actin, microtubules and focal adhesion
8 dynamics during cell migration. *Int. J. Biochem. Cell Biol.*, **35**, 39–50 (2003).
- 9 4. **Petit, V. and Thiery J.-P.:** Focal adhesions: structure and dynamics. *Biol. Cell*, **92**,
10 477–494 (2000).
- 11 5. **Martin, K. H., Slack, J. K., Boerner, S. A., Martin, C. C., and Parsons, J. T.:**
12 Integrin connections map: to infinity and beyond. *Science*, **296**, 1652–1653 (2002).
- 13 6. **Gumbiner, B. M.:** Cell adhesion: the molecular basis of tissue architecture and
14 morphogenesis. *Cell*, **84**, 345–357 (1996).
- 15 7. **Boudreau, N. J. and Jones, P. L.:** Extracellular matrix and integrin signaling: the
16 shape of things to come. *Biochem. J.*, **339**, 481–488 (1999).
- 17 8. **Wozniak, M. A, Modzelewska, K., Kwong, L., and Keely, P. J.:** Focal adhesion
18 regulation of cell behavior. *Biochim. Biophys. Acta*, **1692**, 103–119 (2004).
- 19 9. **Mitra, S. K., Hanson, D. A., and Schlaepfer, D. D.:** Focal adhesion kinase: in
20 command and control of cell motility. *Nat. Rev. Mol. Cell Biol.*, **6**, 56–68 (2005).
- 21 10. **Bae, Y. H., Johnson, P. A., Florek, C. A., Kohn J., and Moghe, P. V.:** Minute
22 changes in composition of polymer substrates produce amplified differences in cell

- 1 adhesion and motility *via* optimal ligand conditioning. *Acta Biomater.* **2**, 473–482
2 (2006).
- 3 11. **Ruoslahti, E. and Obrink, B.:** Common principles in cell adhesion. *Exp. Cell Res.*,
4 **227**, 1–11 (1996).
- 5 12. **Hersel, U., Dahmen, C., and Kessler, H.:** RGD modified polymers: biomaterials
6 for stimulated cell adhesion and beyond. *Biomaterials*, **24**, 4385–4415 (2003).
- 7 13. **Valenick, L. V. and Schwarzbauer, J. E.:** Ligand density and integrin repertoire
8 regulate cellular response to LPA. *Matrix Biol.*, **25**, 223–231 (2006).
- 9 14. **Maheshwari, G., Brown, G., Lauffenburger, D. A., Wells, A., and Griffith, L.G.:**
10 Cell adhesion and motility depend on nanoscale RGD clustering. *J. Cell Sci.*, **113**,
11 1677–1686 (2000).
- 12 15. **Neff, J. A., Tresco, P. A., and Caldwell, K. D.:** Surface modification for controlled
13 studies of cell-ligand interactions. *Biomaterials*, **20**, 2377–2393 (1999).
- 14 16. **Sawyer, A. A., Hennessy, K. M., and Bellis, S. L.:** Regulation of
15 mesenchymal stem cell attachment and spreading on hydroxyapatite by RGD
16 peptides and adsorbed serum proteins. *Biomaterials*, **26**, 1467–1475 (2005).
- 17 17. **Allen, L. T., Tosetto, M., Miller, I. S., O'Connor, D. P., Penney, S. C., Lynch, I.,**
18 **Keenan, A. K., Pennington, S. R., Dawson, K. A., and Gallagher, W. M.:**
19 Surface-induced changes in protein adsorption and implications for cellular
20 phenotypic response to surface interaction. *Biomaterials*, **27**, 3096–3108 (2006).
- 21 18. **Schuler, M., Owen, G. R., Hamilton, D. W., de Wild, M., Textor, M., Brunette,**
22 **D. M., and Tosatti, S. G.:** Biomimetic modification of titanium dental implant
23 model surfaces using RGDSP-peptide sequence. *Biomaterials*, **27**, 4003–4015

- 1 (2006).
- 2 19. **Weisz, O. A. and Schnaar, R.:** Hepatocyte adhesion to carbohydrate-derivatized
3 surfaces I. Surface topography of the rat hepatic lectin. *J. Cell Biol.*, **115**, 485–493
4 (1991).
- 5 20. **Weisz, O. A. and Schnaar, R.:** Hepatocyte adhesion to carbohydrate-derivatized
6 surfaces II. Regulation of cytoskeletal organization and cell morphology. *J. Cell*
7 *Biol.*, **115**, 495–504 (1991).
- 8 21. **Yin, C., Liao, K., Mao, H.-Q., Leong, K. W., Zhuo, R.-X., and Chan V.:**
9 Adhesion contact dynamics of HepG2 cells on galactose-immobilized substrates.
10 *Biomaterials*, **24**, 837–850 (2003).
- 11 22. **Kawase, M., Kurikawa, N., Higashiyama, S., Miura, N., Shiomi, T., Ozawa, C.,**
12 **Mizoguchi, T., and Yagi, K.:** Immobilization of ligand-modified polyamidoamine
13 dendrimer for cultivation of hepatoma cells. *Artif. Org.*, **24**, 18–22 (2000).
- 14 23. **Higashiyama, S., Noda, M., Kawase, M., and Yagi, K.:** Mixed-ligand
15 modification of polyamidoamine dendrimers to develop an effective scaffold for
16 maintenance of hepatocyte spheroids. *J. Biomed. Mater. Res.*, **64A**, 475–482
17 (2003).
- 18 24. **Cho, C. A., Seo, S. J., Park, I. K., Kim, S. H., Kim, T. H., Hoshiba, T. Harada,**
19 **I., and Akaike, T.** Galactose-carrying polymers as extracellular matrices for liver
20 tissue engineering. *Biomaterials*, **27**, 576–585 (2006).
- 21 25. **Park, K.-H., Sung, W. J., Kim S., Kim, D. H., Akaike, T., and Chung, H.-M.:**
22 Specific interaction of mannosylated glycopolymers with macrophage cells
23 mediated by mannose receptor. *J. Biosci. Bioeng.*, **99**, 285–289 (2005).

- 1 26. **Ebeling, P., Koistine, H. A., and Koivisto, V. A.:** Insulin-independent glucose
2 transporter regulates insulin sensitivity. *FEBS Lett.*, **436**, 301–303 (1998).
- 3 27. **Haney, P. M.:** Localization of the GLUT1 glucose transporter to Befeldin
4 A-sensitive vesicles of differentiated CIT₃ mouse mammary epithelial cells. *Cell*
5 *Biol. Int.*, **25**, 277–288 (2001).
- 6 28. **Lizunov, V. A., Matsumoto, H., Zimmerberg, J., Cushman, S. W., and Frolov, V.**
7 **A.:** Insulin stimulates the halting, tethering, and fusion of mobile GLUT4 vesicles
8 in rat adipose cells. *J. Cell Biol.*, **169**, 481–489 (2005).
- 9 29. **Kino-oka, M., Morinaga, Y., Kim, M.-H., Isoda K., , Kawase, M., Yagi, K., and**
10 **Taya, M.:** Morphological regulation of rabbit chondrocytes on glucose-displayed
11 surface. *Biomaterials*, **28**, 1680–1688 (2007).
- 12 30. **Kino-oka, M., Agatahama, Y., Hata, N., and Taya, M.:** Evaluation of growth
13 potential of human epithelial cells by motion analysis of pairwise rotation under
14 glucose-limited condition. *Biochem. Eng. J.*, **19**, 109–117 (2004).
- 15 31. **Pessin, J. E., Thurmond, D. C., Elmendorf, J. S., Coker, K. J., and Okada S.:**
16 Molecular basis of insulin-stimulated GLUT4 vesicle trafficking. *J. Biol. Chem.*,
17 **274**, 2593–2596 (1999).
- 18 32. **Gaudet, C., Marganski, W. A., Kim, S., Brown, C. T., Gunderia, V., Dembo, M.,**
19 **and Wong, J. Y.:** Influence of type I collagen surface density on fibroblast
20 spreading, motility, and contractility. *Biophys. J.*, **85**, 3329–3335 (2003).
- 21 33. **Hata, N., Kim, M.-H., Isoda K., Kino-oka, M., Kawase, M., Yagi, K., and Taya,**
22 **M.:** Dendrimer-immobilized culture surface as a tool to evaluate formation of
23 cellular cytoskeleton of anchorage-dependent cells. *J. Biosci. Bioeng.*, **97**, 222–238

1 (2004).

2 34. **Kim, M.-H., Kino-oka, M., Kawase, M., Yagi, K., and Taya, M.:** Response of
3 human epithelial cells to culture surfaces with varied roughnesses prepared by
4 immobilizing dendrimers with/without D-glucose display. *J. Biosci. Bioeng.*, **103**,
5 111–119 (2007).

6 35. **Cox, E. A., Sastry, S. K., and Huttenlocher, A.:** Integrin-mediated adhesion
7 regulates cell polarity and membrane protrusion through the Rho family of
8 GTPases. *Mol. Biol. Cell*, **12**, 265–277 (2001).

1 **Figure captions**

2 FIG. 1. Time profiles of cellular morphology and roundness of typically selected
3 epithelial cells cultured on various D-glucose-displayed surfaces. (A) 0%
4 D-glucose display; (B) 50% D-glucose display; and (C) 100% D-glucose
5 display. At 24 h of culture time, as indicated by the arrows, insulin (10
6 $\mu\text{g}/\text{cm}^3$) was added to the medium in the flasks.

7 FIG. 2. Efficiency of attachment and overall roundness of epithelial cells cultured
8 on various D-glucose-displayed surfaces in the presence and absence of
9 insulin. The error bars refer to standard deviation, SD ($n = 3$). Symbols:
10 open circles; insulin-free medium, insulin (-); and closed circles;
11 insulin-containing medium, insulin (+).

12 FIG. 3. Effects of GLUT and integrin blockings on efficiency of attachment of
13 epithelial cells cultured on various D-glucose-displayed surfaces. The cells
14 cultured for 24 h were subjected to the tests. The error bars refer to SD (n
15 = 3). Symbols: closed circles, non-blocking; closed triangles,
16 GLUT1-blocking; closed squares, GLUT4-blocking; closed diamonds,
17 GLUT1 and 4-blocking; and closed reverted triangles, integrin
18 $\alpha_5\beta_1$ -blocking.

19 FIG. 4. Effects of GLUT blockings on overall roundness of epithelial cells
20 cultured on various D-glucose-displayed surfaces. The cells cultured for 24
21 h were subjected to the tests. The error bars refer to SD ($n = 3$). Symbols:
22 closed circles, non-blocking; closed triangles, GLUT1-blocking; closed

1 squares, GLUT4-blocking; and closed diamonds, GLUT1 and 4-blocking.

2 FIG. 5. Immunostaining of actin cytoskeleton (green) and vinculin (red) of
3 epithelial cells cultured on various D-glucose-displayed surfaces in the
4 presence of insulin (A, B) and absence of insulin (C, D, E). The images
5 show the representative cells cultivated on the surfaces with 0% (A, C),
6 50% (D) and 100% D-glucose (B, E) display.

7 FIG. 6. Immunostaining of actin cytoskeleton (green), and GLUTs1 and 4 (red) of
8 cells cultured on various D-glucose-displayed surfaces in the presence of
9 insulin (A, B) and absence of insulin (C, D). The images show the top and
10 side (cross-section) views of the representative cells cultured on the
11 surfaces with 0% (A, C) and 100% D-glucose (B, D) display. The white
12 and yellow arrows represent the apical and basal sides of cells,
13 respectively, the latter side being in contact with the culture surface.

14 FIG. 7. Schematic illustration showing possible mechanism of morphological
15 change of epithelial cells in relation to GLUT-mediated anchoring onto
16 D-glucose-displayed surface.