

8. Myung D, Duhamel PE, Cochran JR, Noolandi J, Ta CN, Frank CW. Development of hydrogel-based keratoprostheses: A material perspective. *Biotechnol Prog* 2008; 24:735-41. [PMID: 18422366]
9. Bleckmann H, Holac S. Preliminary results after implantation of four AlphaCor artificial corneas. *Graefes Arch Clin Exp Ophthalmol* 2006; 244:502-6. [PMID: 16133028]
10. Xie RZ, Stretton S, Sweeney DF. Artificial cornea: towards a synthetic onlay for correction of refractive error. *Biosci Rep* 2001; 21:513-36. [PMID: 11900325]
11. Pellegrini G, Traverso CE, Franzi AT, Zingirian M, Cancedda R, De Luca M. Long-term restoration of damaged corneal surfaces with autologous cultivated corneal epithelium. *Lancet* 1997; 349:990-3. [PMID: 9100626]
12. Minami Y, Sugihara H, Oono S. Reconstruction of cornea in three-dimensional collagen gel matrix culture. *Invest Ophthalmol Vis Sci* 1993; 34:2316-24. [PMID: 7685009]
13. Orwin EJ, Hubel A. In vitro culture characteristics of corneal epithelial, endothelial and keratocyte cells in a native collagen matrix. *Tissue Eng* 2000; 6:307-19. [PMID: 10992428]
14. Zhang C, Nie X, Hu D, Liu Y, Deng Z, Dong R, Zhang Y, Jin Y. Survival and integration of tissue-engineered corneal stroma in a model of corneal ulcer. *Cell Tissue Res* 2007; 329:249-57. [PMID: 17453244]
15. Bader A, Schilling T, Teebken OE, Brandes G, Herden T, Steinhoff G, Haverich A. Tissue engineering of heart valves - human endothelial cell seeding of detergent acellularized porcine valves. *Eur J Cardiothorac Surg* 1998; 14:279-84. [PMID: 9761438]
16. Meyer SR, Chiu B, Churchill TA, Zhu L, Lakey JR, Ross DB. Comparison of aortic valve allograft decellularization techniques in the rat. *J Biomed Mater Res A* 2006; 79:254-62. [PMID: 16817222]
17. Grauss RW, Hazekamp MG, van Vliet S, Gittenberger-de Groot AC, DeRuiter MC. Decellularization of rat aortic valve allografts reduces leaflet destruction and extracellular matrix remodeling. *J Thorac Cardiovasc Surg* 2003; 126:2003-10. [PMID: 14688719]
18. Korossis SA, Wilcox HE, Watterson KG, Kearney JN, Ingham E, Fisher J. In-vitro assessment of the functional performance of the decellularized intact porcine aortic root. *J Heart Valve Dis* 2005; 14:408-22. [PMID: 15974537]
19. Hudson TW, Liu SY, Schmidt CE. Engineering an improved acellular nerve graft via optimized chemical processing. *Tissue Eng* 2004; 10:1346-58. [PMID: 15588395]
20. Mertsching H, Walles T, Hofmann M, Schanz J, Knapp WH. Engineering of a vascularized scaffold for artificial tissue and organ generation. *Biomaterials* 2005; 26:6610-7. [PMID: 15979139]
21. Ota T, Taketani S, Iwai S, Miyagawa S, Furuta M, Hara M, Uchimura E, Okita Y, Sawa Y. Novel method of decellularization of porcine valves using polyethylene glycol and gamma irradiation. *Ann Thorac Surg* 2007; 83:1501-7. [PMID: 17383366]
22. Ponce Márquez S, Martínez VS, McIntosh Ambrose W, Wang J, Gantxegui NG, Schein O, Elisseeff J. Decellularization of bovine corneas for tissue engineering applications. *Acta Biomater* 2009; 5:1839-47. [PMID: 19286434]
23. Oh JY, Kim MK, Lee HJ, Ko JH, Wee WR, Lee JH. Processing porcine cornea for biomedical applications. *Tissue Eng Part C Methods*. 2009 [PMID: 19249963]
24. Amano S, Shimomura N, Yokoo S, Araki S, Sasaki K, Yamagami S. Decellularizing corneal stroma using N₂ gas. *Mol Vis* 2008; 14:878-82 [PubMed: 18490960]
25. Zhang C, Nie X, Hu D, Liu Y, Deng Z, Dong R, Zhang Y, Jin Y. Survival and integration of tissue-engineered corneal stroma in a model of corneal ulcer. *Cell Tissue Res* 2007; 329:249-57. [PMID: 17453244]
26. Zhang C, Jin Y, Nie X, Liu Y, Lei J, Hu D. A comparative study on biocompatibility of acellular corneal stroma materials prepared by serial digestion methods. *Zhongguo Xue Fu Chong Jian Wai Ke Za Zhi*. 2006; 20:185-8. [PMID: 16529331]
27. Fujisato T, Minatoya K, Yamazaki S, Meng Y, Niwaya K, Kishida A, Nakatani T, Kitamura S. Preparation and recellularization of tissue engineered bioscaffold for heart valve replacement. In: Mori H, Matsuda H, editors. *Cardiovascular regeneration therapies using tissue engineering approaches*. Tokyo: Springer; 2005. p. 83-94.
28. Gilbert TW, Sellaro TL, Badylak SF. Decellularization of tissues and organs. *Biomaterials* 2006; 27:3675-83. [PMID: 16519932]
29. He H, Adams RM, Farkas DF, Morrissey MT. Use of high-pressure processing for oyster shucking and shelf-life extension. *J Food Sci* 2002; 67:640-5.
30. Calci KR, Meade GK, Tezloff RC, Kingsley DH. High-pressure inactivation of hepatitis A virus within oysters. *Appl Environ Microbiol* 2005; 71:339-43. [PMID: 15640207]

The print version of this article was created on 13 October 2009. This reflects all typographical corrections and errata to the article through that date. Details of any changes may be found in the online version of the article.

ORIGINAL ARTICLE

Azizi Miskon, MEng · Tomo Ehashi, PhD
Atsushi Mahara, PhD · Hiroshi Uyama, PhD
Tetsuji Yamaoka, PhD

Beating behavior of primary neonatal cardiomyocytes and cardiac-differentiated P19.CL6 cells on different extracellular matrix components

Abstract Stem cell-based therapy in cardiac tissue engineering is an emerging field that shows great potential for treating heart diseases. However, even preliminary issues, such as the ideal niche for cardiomyocytes, have not been clarified yet. In the present study, the effects of extracellular matrix (ECM) components on the beating duration of neonatal rat cardiomyocytes (RCMs) and on the cardiac differentiation of P19.CL6 carcinoma stem cells were studied. RCMs were cultured on gelatin-, fibronectin-, and collagen type I-coated dishes and on noncoated polystyrene dishes, and their beating rate, beating duration, and cardiac gene expression were evaluated. The beating period and the expression of troponin T type-2 (TNNT2) and troponin C type-1 (TNNC1) of cardiomyocytes cultured on gelatin-coated dishes were longer and higher than for those on dishes with other coatings. For the cardiac differentiation of P19.CL6 cells, troponin T type-2 expression on gelatin- and fibronectin-coated dishes was five times that on collagen type I-coated dishes or polystyrene dishes 11 days after induction. These results indicate that a gelatin-coated surface has a high ability not only to maintain the cardiac phenotype but also to enhance cardiac differentiation.

Key words Extracellular matrix · Cardiomyocyte · Beating · Differentiation

Introduction

Cardiac tissue engineering, such as cardiomyocyte transplantation for patients with ischemic heart disease or dilated cardiomyopathies, is of great potential therapeutic value to enhance the contractile function of the failing heart. Recently, fetal or neonatal rat cardiomyocytes were reported to form mature cardiac tissue in syngeneic hearts, acutely injured myocardium, and granulation tissue in the heart.¹ However, the best cell sources for clinical cardiomyocyte transplantation are still under debate. In general, three types of potential cell sources have been proposed.² One is the allogeneic source, including human embryonic stem cells or fetal allogeneic cardiomyocytes, but there still remain ethical issues. Another is the transgenic source. Genetically engineered animal cardiomyocytes have been studied in an attempt to reduce the rejection reaction *in vivo*, which is still a long-term problem in recipients.

The most promising cell source is the autogeneic one. Isolating cardiomyocytes from patients' hearts is unrealistic at present, and autologous skeletal muscle precursors, fibroblasts, or mesenchymal stem cells have been studied so far.³ However, since beating cardiomyocytes are more promising,⁴ we have been trying to differentiate bone marrow mesenchymal stem cells (BMSCs) into "beating" cardiomyocytes. There is no certain induction method for BMSC differentiation into beating cardiomyocytes. Many researchers have observed cardiac gene expression in MSCs treated with various inducers⁵⁻⁷ or passage numbers,⁸ but they do not beat spontaneously. Wakitani et al. and Makino et al. reported that murine BMSCs were differentiated to beating cardiomyocyte-like cells *in vitro* by exposing them to DNA-demethylating agent 5-azacytidine.^{5,6} This is in contrast with a report stating that functional cardiac cells and gene expression were not obtained by treatment with 5-azacytidine.⁹

Producing autologous beating cardiomyocytes is thus an attractive goal for cell-based therapy. The crucial part is how to differentiate cells to cardiomyocytes *in vitro* and how to maintain the beating. Various microenvironments surrounding the cells (niches) play important roles not only

Received: September 5, 2008 / Accepted: January 14, 2009

A. Miskon · T. Ehashi · A. Mahara · T. Yamaoka (✉)
Department of Biomedical Engineering, Advanced Medical
Engineering Center, National Cardiovascular Center Research
Institute, 5-7-1 Fujishiro-dai, Suita, Osaka 565-8565, Japan
Tel. +81-6-6833-5012 ext. 2637; Fax +81-6-6835-5476
e-mail: yamtet@ri.ncvc.go.jp

A. Miskon · H. Uyama
Department of Chemical Engineering, Osaka University, Osaka,
Japan

in cell proliferation but also in cell differentiation. The effect of extracellular matrix (ECM) proteins such as collagen type I, collagen type IV, gelatin, laminin, fibronectin, Matrigel (a mixture of laminin, collagen type IV, heparan sulfate proteoglycans, and entactin), and Cardiogel (a mixture of collagen types I and III, glycoproteins, laminin, fibronectin, and proteoglycans) on cell viability, proliferation rate, and cardiomyocyte gene expression have been reported;^{10,11} however, the cardiomyocyte beating behavior has not fully been discussed.

In the present study, differentiation to beating cardiomyocytes and the beating duration of the cardiomyocytes were studied using two types of model cells. Murine embryonal carcinoma (EC) stem cells (P19.CL6),¹² which are widely used for investigating cardiac differentiation, were treated with differentiation medium containing 1% dimethyl sulfoxide (DMSO) on various ECM proteins (collagen, type I gelatin, and fibronectin), and their differentiation efficiency was evaluated. The effect of these substrates on the beating duration of rat neonatal cardiomyocytes was also investigated, along with intracellular cardiac marker genes [troponin T type-2 (TNNT2) and troponin C type-1 (TNNC1)]¹³ and skeletal muscle marker gene [troponin C type-2 (TNNC2)], which is reported to be expressed in the early developing heart.¹⁴ Any fundamental information obtained would be important for the cardiac differentiation of various stem cells, including autologous BMSCs.

Materials and methods

Cardiomyocytes

Cardiomyocytes were isolated from neonatal Sprague-Dawley rat heart (1 to 2 days old) by the collagenase digestion method with modifications.^{15,16} Institutional guidelines for the care and use of laboratory animals were observed. The hearts were removed and carefully minced with a scalpel blade into fragments and were rinsed several times with Hanks' balanced salt solution (Sigma-Aldrich, St. Louis, MO, USA) to remove blood and cellular debris. The minced hearts were gently stirred in 50 ml collagenase solution [0.15 M Sodium Chloride (NaCl), 5.63 mM Potassium Chloride (KCl), 0.02 M 4-(2-hydroxyethyl)-1-piperazineethanesulfonic acid (HEPES), 0.02 M Sodium Hydrogen Carbonate (NaHCO₃), 3.74 mM Calcium Chloride Dihydrate (CaCl₂·2H₂O), and 6.5 × 10⁴ U collagenase (Wako, Osaka, Japan, Lot no: 06032W)] at 37°C for 30 min. The resulting cell suspension was filtered through a nylon cell strainer (BD Falcon, BD Biosciences, Bedford, MA, USA) with a 40-μm pore size and centrifuged at 78 g for 3 min.

Isolated cardiomyocytes (1.0 × 10⁵) were cultured in minimum essential medium alpha medium (α-MEM, Gibco, Invitrogen, Grand Island, NY, USA) supplemented with 10% (v/v) fetal bovine serum (FBS, MP Biomedicals, Eschwege, Germany, lot no: 7297H), and 100 IU/l penicillin-streptomycin (Wako, Osaka, Japan) on 60-mm gelatin-

(IWAKI, Asahi Glass, Tokyo, Japan), fibronectin-(BD Falcon, BD BioCoat, BD Biosciences), or collagen type I-coated dishes and noncoated polystyrene dishes (IWAKI).

Differentiation of P19.CL6 cells

Differentiation of P19.CL6 cells was performed as described by Ohkubo with modifications.¹² Briefly, P19.CL6 cells were plated at a density of 3.7 × 10⁵ cells on 60-mm gelatin-, fibronectin-, or collagen type I-coated dishes or noncoated polystyrene dishes with a α-MEM supplemented with 10% (v/v) FBS containing 1% DMSO (Wako). As a control experiment, P19.CL6 cells were cultured with α-MEM supplemented with 10% (v/v) FBS without 1% DMSO. The medium was changed every 2 days.

Measurement of action potential

Cultured plates on which beating colonies appeared were placed on the stage of an inverted phase-contrast optical microscope (ZEISS, Axiovert 135, Munich, Germany) and action potentials were measured immediately by a conventional microelectrode. The measurements were conducted after 1, 2, and 3 weeks of cultivation. Silicon-coated Ag wire (A-M System, Carlsborg, WA, USA, 250 μm bare, 330 μm coated) was used as the microelectrode. The microelectrode was set in a micromanipulator system (MON-202D, Nikon Narishige, Tokyo, Japan) and connected to a bioelectric amplifier (AB-621G, Nihon Kohde, Osaka, Japan). The sensitivity and time constant of the bioelectric amplifier were set at 0.1 mV/div and 0.003 s. For the measurements, the microelectrode was adjusted using the micromanipulator until it was attached to the membrane of beating cells. The voltage difference was amplified by the bioelectric amplifier and was displayed and recorded using Chart 5 software (AD Instrument, Bella Vista, Australia).

Total RNA isolation and reverse transcription

Total RNAs of cardiomyocytes and DMSO-treated P19.CL6 cells cultured on various dishes were extracted by QuickGene RNA cultured cell kit S (Fujifilm Life Science, Tokyo, Japan) 4 weeks after culture and 11 days after culture, respectively.

First-strand cDNAs were synthesized using a mixture of oligo(dT)₁₈ primer. Total cellular RNAs (200 ng) were incubated with 2.5 μM oligo(dT)₁₈ primer at 70°C for 10 min to denature the RNA secondary structure and then incubated at 4°C to let the primer anneal to the RNA. A given amount of 5X RT buffer (Toyobo, Osaka, Japan) and 2.5 mM Deoxynucleotide Trisphosphate (dNTP) mixture (Takara Bio, Shiga, Japan) (4 μl) were added and incubated at 37°C for 5 min. The reverse transcriptase (100 Units, Toyobo) was added into the mixture and the reverse transcriptase (RT) reaction was extended at 37°C for 1 h. Then, the reac-

Table 1. Polymerase chain reaction primers used in this study

| Genes | Sense | Antisense |
|-------|------------------------------|-------------------------------|
| TNNT2 | 5'-GAAACAGGATCAACGACAACCA-3' | 5'-CGCCCGGTGACTTTGG-3' |
| TNNC1 | 5'-GATCTCTCCGCATGTTTGACA-3' | 5'-TGGCCTGCAGCATCATCTT-3' |
| TNNC2 | 5'-AGATCGAATCCCTGATGAAGGA-3' | 5'-CATCTTCAGAAACTCGTGAAGTC-3' |
| GAPDH | 5'-CTACCCCAATGTATCCGTTGT-3' | 5'-TAGCCCAGGATGCCCTTATAGT-3' |

GAPDH, Glyceraldehyde 3 phosphate dehydrogenase

Table 2. Summary of voltage potentials for cardiomyocytes cultured in several types of extracellular matrix-coated dishes

| Substrate | Action potential (mV) [Beating rate (Hz)] | | |
|-----------------|---|-------------------------|-------------------------|
| | Day 7 | Day 14 | Day 21 |
| Gelatin | 6.7 ± 0.49 [1.2 ± 0.05] | 6.6 ± 1.26 [1.3 ± 0.01] | 3.1 ± 0.21 [2.8 ± 0.03] |
| Fibronectin | 1.1 ± 0.97 [1.1 ± 0.30] | 6.9 ± 1.15 [1.3 ± 0.42] | 2.8 ± 0.11 [2.0 ± 0.11] |
| Collagen type-I | 2.6 ± 0.35 [0.8 ± 0.02] | 1.7 ± 0.03 [2.3 ± 0.05] | ND |
| Polystyrene | 2.0 ± 0.75 [0.3 ± 0.04] | ND | ND |

ND, not done

tion mixture was heated at 94°C for 5 min to inactivate the enzyme and cooled at 4°C for 15 min. The RNase (DNase-free, 0.5 µg, Roche Diagnostics, Mannheim, Germany) was added to the mixture and incubated at 37°C to remove the template of RNA.

Real-time quantitative polymerase chain reaction

Real-time quantitative polymerase chain reaction (PCR) was conducted with SYBR Green. Primers for PCR analysis for troponin T type-2, troponin C type-1, and troponin C type-2 were designed using Primer Express software (Perkin-Elmer Applied Biosystems, Warrington, UK). The primer sequences are shown in Table 1. The reaction mixtures contained 23.74 µl distilled water, 25 µl SYBR Green Realtime PCR master mix (Toyobo), 100 nM of each primer, and 0.26 µl cDNA. The thermal profile for PCR was 50°C for 2 min, followed by 95°C for 10 min, followed by 40 cycles of 15 s at 95°C and 1 min at 60°C. Distilled water 0.26 µl was used as a negative control PCR reaction to ensure the absence of template contamination in PCR reagents. The average threshold cycle (Ct) values of triplicate measurements were used for all subsequent calculations on the basis of the delta Ct method.

Results

Beating behavior of isolated cardiomyocytes

One week after culture, the action potential of cardiomyocytes on gelatin-coated dishes was higher than that for other conditions (Fig. 1), and the beating duration was also longer than that for other conditions. The action potential and beating rates on each matrix are summarized in Table 2. After 7 days of culture, the action potential was around 6.7 ± 0.49 mV for cardiomyocytes cultured on gelatin-coated dishes, 1.1 ± 0.97 mV on fibronectin-coated dishes, 2.0 ±

0.35 mV on collagen type I-coated dishes, and 2.0 ± 0.75 mV on noncoated polystyrene dishes. These results indicate that the beating rate on fibronectin-coated dishes, collagen type I-coated dishes, and noncoated polystyrene dishes were 84%, 61%, and 70% lower than the beating rate on gelatin-coated dishes after 1 week of cultivation.


After 14 days of culture, the action potential became 6.6 ± 1.26 mV on gelatin-coated dishes, 6.9 ± 1.15 mV on fibronectin-coated dishes, and 1.7 ± 0.03 mV on collagen type I-coated dishes. No beating was observed on noncoated polystyrene dishes after 2 weeks of cultivation. After 21 days of culture, the action potential was 3.1 ± 0.21 mV on gelatin-coated and 2.8 ± 0.11 mV on fibronectin-coated dishes. No action potential was detected on collagen type I-coated dishes and polystyrene dishes.

The beating rate of cardiomyocytes was also affected by the ECM proteins. After 7 days of culture, the beating rate of cardiomyocytes was 1.2 ± 0.05 Hz on gelatin-coated dishes, 1.1 ± 0.3 Hz on fibronectin-coated dishes, 0.8 ± 0.02 Hz on collagen type I-coated dishes, and 0.3 ± 0.04 Hz on noncoated polystyrene dishes. After 14 days of culture, the beating rate became 1.3 ± 0.01 Hz on gelatin-coated dishes, 1.3 ± 0.42 Hz on fibronectin-coated dishes, and 2.3 ± 0.05 Hz on collagen type I-coated dishes. After 21 days, the beating rate was 2.8 ± 0.03 Hz on gelatin-coated dishes and 2.0 ± 0.11 Hz on fibronectin-coated dishes, whereas cardiomyocytes cultured on noncoated polystyrene dishes and collagen-coated dishes did not beat well and stopped at an early stage of cultivation. These results indicate that gelatin could maintain the beating behavior of cardiomyocytes for a longer time compared to fibronectin or collagen type I.

Expression of troponin T type-2 and troponin C type-1

Cardiac troponin T type-2 and troponin C type-1 are known to be cardiomyocyte markers and are important in the structure of muscle tissue; they also play a role in the contraction of muscle cells.¹³ After 4 weeks of culture,

Fig. 1. Electrophysiological assessment of isolated cardiomyocytes after 7 and 21 days of cultivation on different substrates



expression of troponin T type-2 in cardiomyocytes on gelatin-coated dishes was 7, 6, and 12 times higher than those on fibronectin-coated, collagen-coated, and non-coated dishes (Fig. 2A). Expression of troponin C type-1 on gelatin-coated dishes was also 5, 6, and 32 times higher than those on fibronectin-coated, collagen type I-coated, and noncoated dishes (Fig. 2B). These results are consistent with the results of the electrophysiological study (Fig. 1), in which the beating of cardiomyocytes still could be detected on gelatin- and fibronectin-coated dishes after 3 weeks of cultivation.

Differentiation of P19.CL6 cells

Beating colonies were found on gelatin-coated dishes in 9 days with α -MEM medium containing 1% DMSO. This was followed by cells cultured on fibronectin-coated dishes after 10 days of culture and collagen type I-coated dishes after 11 days of culture. The average number of beating colonics found on the first day of detection was 13 ± 7 colonies per dish on gelatin-coated dishes, 9 ± 5 colonies per dish on

fibronectin-coated dishes, 5 ± 2 colonies on collagen type I-coated dishes, and 3 ± 1 colonies on polystyrene dishes (Table 3).

As described earlier, troponin T type-2 and troponin C type-1 are known to be markers of cardiomyocytes,¹³ and troponin C type-2 is reported to be a marker of cardiac development.¹⁴ Expression of troponin T type 2 on gelatin- and fibronectin-coated dishes was higher than that for the other dishes, as shown in Fig. 3A. However, the expression of troponin C type-2 in collagen type I-coated dishes and noncoated polystyrene dishes was higher than that in gelatin- and fibronectin-coated dishes. The high expression of troponin C type-2 on collagen type I coated dishes and noncoated polystyrene dishes on day 11 was possibly because of the delayed differentiation of P19.CL6 cells to cardiomyocytes-like cells. Stoutamyer and Dhoot reported that troponin C type-2 was first expressed on day 3, reached maximum expression on day 5, and decreased day by day until no expression was found on day 11 during the development of quail heart in ovo.¹⁴ Stoutamyer and Dhoot also reported that the expression of troponin C type-1 was detected on day 2 and decreased during the increase of




Fig. 2. Expression of cardiac markers (**A** troponin T type-2 and **B** troponin C type-1) in isolated cardiomyocytes after cultivation for 4 weeks on various types of extracellular matrix. *GAPDH*, Glyceraldehyde 3 phosphate dehydrogenase; *PS*, polystyrene

Table 3. Number of beating colonies of P19.CL6 cells 11 days after induction with 1% dimethyl sulfoxide

| Substrate | Average number of beating colonies per dish |
|-----------------|---|
| Gelatin | 13 ± 7 |
| Fibronectin | 9 ± 5 |
| Collagen type-I | 5 ± 2 |
| Polystyrene | 3 ± 1 |

troponin C type-2, reaching a constant level after that.¹⁴ In addition, the troponin C type-2 expression on a collagen-coated or noncoated dish may suggest skeletal muscle differentiation of P19.CL6 cells, although further analysis is needed.

These results demonstrated that differentiation of P19.CL6 cells to beating cells on gelatin-coated dishes and fibronectin-coated dishes was faster and more effective than that on collagen type I-coated dishes and noncoated polystyrene dishes.

Discussion

In the present study, enhanced action potentials and elongated beating durations of neonatal cardiomyocyte were observed on gelatin-coated dishes compared to those on collagen type I-coated dishes. Possible differences between gelatin and collagen are: (1) collagen possesses a triple-helical conformation, (2) gelatin has a wide molecular weight distribution depending on its preparation process, (3) gelatin




Fig. 3. Expression of cardiac markers in P19.CL6 cells (**A** troponin T type-2, **B** troponin C type-1, **C** troponin C type-2) treated with minimum essential medium alpha medium (α -MEM) containing 1% dimethyl sulfoxide on various dishes (white bars) or with α -MEM as a control for 11 days (black bars) PS, polystyrene

is easily hydrolyzed by protease,¹⁷ (4) the dynamic storage modulus of gelatin is higher than that of collagen,¹⁸ and (5) gelatin binds with fibronectin with a higher affinity.¹⁹⁻²¹ It has already been reported that fibronectin is a very elastic substrate.²²

The mechanism of the elongated beating duration on gelatin-coated substrate is unclear, but the mechanical properties (elasticity) and biological activity of the substrates might be influential. It has been reported that the mechanical properties of culture matrices affect various cellular properties such as the morphology of embryonic stem cells,^{23,24} the collagen production of fibroblasts,^{25,26} and the differentiation of mesenchymal and neural stem cells.^{27,28}

Fibronectin produced by culture cells is known to associate with the fibronectin-binding domain of collagen, resulting in fibrillogenesis.²¹ It has also been reported that fibronectin binds to gelatin more strongly than to collagen.^{20,21} Therefore, the high production of fibrils might occur more effectively on gelatin-coated dishes than on fibronectin- or collagen-coated dishes. These connecting elastic fibers might regulate the motion of cardiomyocytes during

contraction and recoil, as suggested by Ahumada and Saffitz.²⁹ The highly elastic features of matrices made of gelatin, fibronectin bound onto gelatin,^{18,22} and developed fibrin matrices may allow easier contraction of cardiomyocytes, leading to larger action potentials and longer beating durations on gelatin.

P19.CL6 cells were used to study the effect of culture substrates on cardiogenesis *in vitro* because Ohkubo reported that P19.CL6 cells differentiated into cardiomyocytes in 10 days after DMSO treatment, and observation of differentiation continued for 11 days. The first beating colony was found on the 9th day on gelatin-coated dishes, on the 10th day on fibronectin-coated dishes, and on the 11th day on collagen type I-coated dishes and noncoated polystyrene dishes. The expressions of troponin T type-2 on gelatin- and fibronectin-coated dishes were significantly higher than those on collagen type I-coated dishes and on noncoated polystyrene dishes. High expression of troponin C type-2 in collagen type I-coated dishes and noncoated polystyrene dishes is considered to indicate delayed cardiac differentiation or skeletal muscle differentiation of P19.CL6.

The differentiation of P19.CL6 cells on gelatin- and collagen type I-coated dishes was very different, despite their similar unit structure. The fast differentiation on gelatin was possibly because of slow cell proliferation on high-dynamic-storage-modulus substrates.¹⁸ The growth of P19.CL6 cells on gelatin-coated dishes was about half that on collagen type I-coated dishes (data not shown). Walsh et al. suggested that the proliferation of mesenchymal stem cells was suppressed during the differentiation to osteoblasts *in vitro*.³⁰ The fast differentiation on fibronectin-coated dishes may also relate to the elasticity of the substrate.²²

This finding will hopefully offer a bright future for the myocardial patch scaffold. It has been reported that the probability of cardiac differentiation of adipose tissue-derived mesenchymal stem cells after transplantation to infarcted rat heart is quite low.³¹ In the present study, the gelatin-based niche was found to be preferable for cardiac differentiation and for the beating function of cardiomyocytes. We will be applying these results to the cardiac differentiation of mesenchymal stem cells in order to prepare allogeneic beating cardiomyocytes.

Conclusion

The physical and biological properties of the substrate were the important factors not only for maintaining cardiac functions but also for leading to the cardiac differentiation of P19.CL cells. Gelatin was found to be a promising ECM protein to this end *in vitro*.

Acknowledgments This work was partly supported by a Grant-in-Aid for Scientific Research (B) from the Ministry of Education, Culture, Sports, Science and Technology of Japan. The author (Azizi Miskon) would like to thank the Ministry of Higher Education, Malaysia, and Tun Hussein Onn of the University of Malaysia for funding his study under the Academic Training Scheme.

References

- Li RK, Mickle DA, Weisel RD, Zhang J, Mohabeer MK. *In vivo* survival and function of transplanted rat cardiomyocytes. *Circ Res* 1996;78:283–288
- El Oakley RM, Ooi OC, Bongso A, Yacoub MH. Myocyte transplantation for myocardial repair: a few good cells can mend a broken heart. *Ann Thorac Surg* 2001;71:1724–1733
- Ott HC, Davis BH, Taylor DA. Cell therapy for heart failure – muscle, bone marrow, blood, and cardiac-derived stem cells. *Semin Thorac Cardiovasc Surg* 2005;17:348–360
- Segers VF, Lee RT. Stem-cell therapy for cardiac disease. *Nature* 2008;451:937–942
- Makino S, Fukuda K, Miyoshi S, Konishi F, Kodama H, Pan J, Sano M, Takahashi T, Hori S, Abe H, Hata J, Umezawa A, Ogawa S. Cardiomyocytes can be generated from marrow stromal cells *in vitro*. *J Clin Invest* 1999;103:697–705
- Wakitani S, Saito T, Caplan AI. Myogenic cells derived from rat bone marrow mesenchymal stem cells exposed to 5-azacytidine. *Muscle Nerve* 1995;18:1417–1426
- Xu W, Zhang X, Qian H, Zhu W, Sun X, Hu J, Zhou H, Chen Y. Mesenchymal stem cells from adult human bone marrow differentiate into a cardiomyocyte phenotype *in vitro*. *Exp Biol Med* 2004;229:623–631
- Zhang FB, Li L, Fang B, Zhu DL, Yang HT, Gao PJ. Passage-restricted differentiation potential of mesenchymal stem cells into cardiomyocyte-like cells. *BBRC* 2005;336:784–792
- Liu Y, Song J, Liu W, Wan Y, Chen X, Hu C. Growth and differentiation of rat bone marrow stromal cells: does 5-azacytidine trigger their cardiomyogenic differentiation? *Cardiovasc Res* 2003;58:460–468
- Macfelda K, Kapeller B, Wilbacher I, Losert UM. Behavior of cardiomyocytes and skeletal muscle cells on different extracellular matrix components – relevance for cardiac tissue engineering. *Artif Organs* 2007;31:4–12
- Bird SD, Doevendans PA, van Rooijen MA, Brutel de la Riviere A, Hassink RJ, Passier R, Mummery CL. The human adult cardiomyocyte phenotype. *Cardiovasc Res* 2003;58:423–434
- Ohkubo AH. Differentiation of beating cardiac muscle cells from a derivative of P19 embryonal carcinoma cells. *Cell Struct Funct* 1996;21:101–110
- Saggin L, Ausoni S, Gorza L, Sartore S, Schiaffino S. Troponin T switching in the developing rat heart. *J Biol Chem* 1998;263:18488–18492
- Stoutamyer A, Dhoot GK. Transient expression of fast troponin C transcripts in embryonic quail heart. *J Muscle Res Cell Motil* 2005;26:237–245
- Seglen PO. Preparation of isolated rat liver cells. *Methods Cell Biol* 1976;13:29–83
- Moldeus P, Höberg J, Orrenius S. Isolation and use of liver cells. *Methods Enzymol* 1978;52:60–71
- Zhang Z, Li G, Shi B. Physicochemical properties of collagen, gelatin, and collagen hydrolysate derived from bovine lamed split wastes. *J Soc Leather Technol Chem* 2006;90:23–28
- Chien JC, Chang EP. Dynamic mechanical and rheo-optical studies of collagen and gelatin. *Biopolymers* 1972;11:2015–2031
- Little CD, Chen WT. Masking of extracellular collagen and the co-distribution of collagen and fibronectin during matrix formation by cultured embryonic fibroblast. *J Cell Sci* 1982;55:35–50
- Engvall E, Ruoslahti E, Miller ED. Affinity of fibronectin to collagens of different genetic types and to fibrinogen. *J Exp Med* 1978;147:1584–1595
- Dzamba BJ, Wu H, Jaenisch R, Peters DM. Fibronectin binding site in type I collagen regulates fibronectin fibril formation. *J Cell Biol* 1993;121:1165–1172
- Erickson HP. Stretching fibronectin. *J Muscle Res Cell Motil* 2002;23:575–580
- Bard JB, Hay ED. The behavior of fibroblasts from the developing avian cornea. Morphology and movement *in situ* and *in vitro*. *J Cell Biol* 1975;67:400–418
- Hay ED. Interaction of embryonic surface and cytoskeleton with extracellular matrix. *Am J Anat* 1982;165:1–12


25. Nakagawa S, Pawelek P, Grinnell F. Extracellular matrix organization modulates fibroblast growth and growth factor responsiveness. *Exp Cell Res* 1989;182:572-582
26. Halliday NL, Tomasek JJ. Mechanical properties of the extracellular matrix influence fibronectin fibril assembly in vitro. *Exp Cell Res* 1995;217:109-117
27. Engler AJ, Sen S, Sweeney HL, Discher DE. Matrix elasticity directs stem cell lineage specification. *Cell* 2006;126:677-689
28. Saha K, Keung AJ, Irwin EF, Li Y, Little L, Schaffer DV, Healy KE. Substrate modulus directs neural stem cell behavior. *Biophys J* 2008;95:4426-4438
29. Ahumada GG, Saffitz JE. Fibronectin in rat heart: a link between cardiac myocytes and collagen. *J Histochem Cytochem* 1984;4: 383-388
30. Walsh S, Jordan GR, Jefferiss C, Stewart K, Beresford JN. High concentrations of dexamethasone suppress the proliferation but not the differentiation or further maturation of human osteoblast precursors in vitro: relevance to glucocorticoid-induced osteoporosis. *Rheumatology* 2001;40:74-83
31. Miyahara Y, Nagaya N, Kataoka M, Yanagawa B, Tanaka K, Hao H, Ishino K, Ishida H, Shimizu T, Kangawa K, Sano S, Okano T, Kitamura S, Mori H. Monolayered mesenchymal stem cells repair scarred myocardium after myocardial infarction. *Nat Med* 2006;12: 459-465

In Vivo Tissue Response and Degradation Behavior of PLLA and Stereocomplexed PLA Nanofibers

Daisuke Ishii, Tang Hui Ying, Atsushi Mahara, Sunao Murakami, Tetsuji Yamaoka, Won-ki Lee, and Tadahisa Iwata

Biomacromolecules, 2009, 10 (2), 237-242 • DOI: 10.1021/bm8009363 • Publication Date (Web): 31 December 2008

Downloaded from <http://pubs.acs.org> on February 18, 2009



More About This Article

Additional resources and features associated with this article are available within the HTML version:

- Supporting Information
- Access to high resolution figures
- Links to articles and content related to this article
- Copyright permission to reproduce figures and/or text from this article

[View the Full Text HTML](#)

In Vivo Tissue Response and Degradation Behavior of PLLA and Stereocomplexed PLA Nanofibers

Daisuke Ishii,^{†,‡} Tang Hui Ying,^{†,§,||} Atsushi Mahara,[†] Sunao Murakami,[†] Tetsuji Yamaoka,[†] Won-ki Lee,[∇] and Tadahisa Iwata^{*,†,○}

Polymer Chemistry Laboratory, RIKEN Institute, 2-1 Hirosawa, Wako-shi, Saitama 351-0198, Japan, School of Biological Science, Universiti Sains Malaysia, 11800 Penang, Malaysia, Department of Biomedical Engineering, Advanced Medical Engineering Center, National Cardiovascular Center Research Institute, 5-7-1 Fujishirodai, Suita, Osaka 565-8565, Japan, and Division of Chemical Engineering, Pukyong National University, San 100, Yongdang-dong, Nam-gu, Busan 608-739, Republic of Korea

Received August 21, 2008; Revised Manuscript Received November 24, 2008

Biocompatibility of PLLA and stereocomplexed PLA nanofibers was evaluated by subcutaneous implantation in rats for 4–12 weeks. Characterization of the nanofibers was performed by GPC, SEM, wide-angle X-ray diffraction, and optical microscopy of hematoxylin-eosin stained ultrathin sections of explanted nanofibers. Stereocomplexed PLA nanofiber showed slower degradation than PLLA nanofiber and thus retained their shape after prolonged implantation. Furthermore, stereocomplexed PLA nanofiber caused milder inflammatory reaction than PLLA nanofiber. These results offer the potential use of PLLA and stereocomplexed PLA nanofibers as a biomaterial for short-term and long-term tissue regeneration, respectively. Stereocomplexed PLA nanofiber after *in vitro* degradation showed smaller degree of swelling than PLLA nanofiber. Taking the results of *in vivo* degradation together with *in vitro* degradation into consideration, bioabsorption mechanism of the *in vivo* degradation of the nanofibers is proposed.

Introduction

In the field of medical sciences, the method of tissue engineering has been extensively studied to overcome the problems of conventional methods such as organ transplantation and usage of artificial organs.¹ In tissue engineering, the proliferation and differentiation of cultured cells for deficiency repair has to be artificially controlled. The development of scaffold materials on which cells proliferate and differentiate has been a major concern in tissue engineering. Conventionally, collagens and gelatins extracted from animals have been used to produce scaffolds. However, the usage of these animal-origin materials is shrinking for fear of infectious diseases. Alternatively, the usage of biodegradable and biocompatible polymers that do not contain infectious substances such as endotoxins and prions has been explored.

Recently, as a novel method for producing scaffolds, formation of nanofibers with the diameter ranging from several tens to hundreds of nanometers is extensively studied.^{2–4} Nanofiber scaffolds have fine pores and grooves as small as a few micrometers wide. Such fine structural features facilitate the adhesion and proliferation of cells. It is required for nanofiber scaffolds to sustain sufficient strength to support regenerating

tissue cells and to be degraded after the tissue regeneration is completed. To meet these demands, various kinds of biodegradable and biocompatible polymers have been processed into nanofibers. Furthermore, the fiber morphology, crystalline structure, and degradation behavior of the nanofibers have been investigated.^{5–7}

Poly(lactide) (PLA) is one of a few polymers that is practically applied as various medical materials such as implants and sutures.⁸ PLA possesses mechanical properties sufficient to endure the mechanical load applied in human body. However, it is readily hydrolyzed both in enzymatic and nonenzymatic conditions.⁹ The high susceptibility of PLA toward hydrolysis becomes a shortcoming when the long-time storage under physiological conditions is required. Various efforts to overcome this shortcoming have been attempted. One of such efforts is the formation of stereocomplex in PLA materials.

Stereocomplexed PLA is a characteristic crystalline form of PLA.^{10,11} A sterically stable racemic crystal of stereocomplexed PLA is formed by complexing poly(L-lactide) (PLLA) and poly(D-lactide) (PDLA) that take molecular conformations of left-handed and right-handed helices, respectively.¹² As a result, stereocomplexed PLA has a melting temperature of 230 °C, that is 50 °C higher than PLLA and PDLA.¹⁰ Furthermore, it has been reported that stereocomplexed PLA is more stable against hydrolysis than PLLA.^{13–15} This finding offers the possibility for controlling the hydrolytic behavior of PLA material by the formation of stereocomplex. Although various methods have been proposed and investigated for the formation of stereocomplex within PLA materials,^{16,17} PLA materials that contain only racemic crystal has not yet been processed. Furthermore, the conventional processes involve long-time annealing at elevated temperatures as high as 180 °C and repeated stretching. To form stereocomplexed PLA more conveniently, electrospinning has recently been applied to the formation of stereocomplexed

* To whom correspondence should be addressed. Tel.: +81-3-5841-7888. Fax: +81-3-5841-1304. E-mail: atiwata@mail.ecc.u-tokyo.ac.jp.

[†] RIKEN Institute.

[‡] Present affiliation and address: Department of Materials Chemistry, Faculty of Science and Technology, Ryukoku University 1-5 Yokotani, Seta Oe-cho, Otsu-shi, Shiga 520-2194, Japan.

[§] Universiti Sains Malaysia.

^{||} Present affiliation and address: Bioengineering Laboratory, RIKEN Institute, 2-1 Hirosawa, Wako-shi, Saitama 351-0198, Japan.

[∇] National Cardiovascular Center Research Institute.

[○] Pukyong National University.

[○] Present affiliation and address: Graduate School of Agricultural and Life Sciences, The University of Tokyo, 1-1-1 Yayoi, Bunkyo-ku, Tokyo 113-8657, Japan.

PLA.¹⁸ In particular, we have first succeeded in processing stereocomplexed PLA nanofiber in which the racemic crystal is only the crystalline polymorph.¹⁹ The formation of racemic crystal was performed by annealing the as-spun nanofiber at 100 °C, which is 80 °C lower than those in previously reported studies.

The degradation behavior of PLA nanofibers has been investigated by using various specimens and conditions.^{20–22} However, the previous reports were all limited to *in vitro* conditions. There have been no reports on the biocompatibility and *in vivo* degradation behavior of stereocomplexed PLA nanofibers.

In this work, tissue responses and degradation behavior of PLLA and stereocomplexed PLA nanofibers *in vivo* were investigated by subcutaneously implanting these nanofibers in rats. The tissue response against the nanofibers has been investigated by means of histological observation. The changes in structure and properties of the nanofibers during subcutaneous implantation has been investigated using scanning electron microscopy (SEM), wide-angle X-ray diffraction (WAXD), gel permeation chromatography (GPC), and mechanical tensile testing. The relation between tissue response and degradation behavior of nanofibers is discussed in terms of the structural and property changes of the nanofibers.

Experimental Section

Materials. PLLA with a M_n of 4.7×10^5 and M_w/M_n of 1.8 was purchased from Polysciences, Inc. and used as received. PDLA with a $M_n = 2.2 \times 10^5$ and M_w/M_n of 1.5 was synthesized according to the following procedure. The D-lactide monomer, obtained from Purac, was recrystallized from anhydrous ethyl acetate. Bulk polymerizations were carried out in glass ampoules containing a magnetic stirring bar at 130 °C. Stannous octanoate in petroleum ether was used as the catalyst for the ring-opening polymerization. The ampoules were evacuated using a high vacuum pump and repeatedly flushed with high purity nitrogen to remove volatile impurities, solvents, and oxygen. Then the ampoules were sealed with a blowtorch and heated to the reaction temperature. The products in the ampoules were dissolved in chloroform, precipitated in the excess of methanol, filtered, and dried.

Electrospinning. Solutions of PLLA and PDLA (1 wt %) were prepared using 1,1,1,3,3,3-hexafluoro-2-propanol, HFIP, as the solvent. For the preparation of PLA stereocomplex nanofibers, equal volume of PLLA and PDLA solutions were mixed for several seconds by vortex mixer. Nanofibers were prepared using an Esprayer ES-2000 electrospinning device by Fulence, Co. Ltd. Dope solutions were extruded with a speed of 2.4 mL/h from a syringe needle with an inner diameter of 0.5 mm. Electrical voltage of 15 kV was applied to the syringe. Nanofibers were deposited onto a 10×10 cm² aluminum substrate placed perpendicular to the needle. To ensure sufficient thickness of nanofiber mats, the substrate was covered with a template made by a 51.4 μm thick Kapton film on which a 3×3 cm² window was opened. Distance between the needle tip and the substrate was set to 15 cm. The atmosphere of the spinning chamber was kept at less than 30% of relative humidity. PLLA and PLA stereocomplex nanofibers were then annealed in an oven at 100 °C for 8 h. Each electrospun PLA nanofiber mats was then cut into two different dimensions measuring 1×1 cm² and 1×3 cm², respectively. To prevent contamination, all scaffolds were sterilized overnight with ethylene oxide at 40 °C and kept in sealed bags until use.

Subcutaneous Implantation in Rat and Retrieval. Two 12-week old male Wistar rats were used for implanting the scaffolds; one for scaffolds measuring 1×1 cm², while the other for scaffolds measuring 1×3 cm². The experimental protocol had been approved by the Animal Care Committee of the National Cardiovascular Center, Osaka, Japan. The implantation of nanofiber mat was performed under anesthesia

using diethyl ether. The 1×1 cm² scaffolds were implanted subcutaneously at one side of the backbone while the 1×3 cm² scaffolds were implanted subcutaneously at the backbone. The grouping of the rats was based on the duration of observation for 4 weeks and 12 weeks.

Upon explantation, the nanofiber mats measuring 1×1 cm² were excised with the surrounding tissues and stored in 2.5% glutaraldehyde in phosphate buffer saline (PBS) with a pH of 7 until further preparation of ultrathin section for histological observation. The retrieved 1×3 cm² nanofiber mats were treated with 1.25 wt % trypsin solution to remove the surrounding tissues. They were then kept in tubes containing PBS at 4 °C until further use. Trace amount of sodium azide was added to avoid the decay of the specimens. After trypsin treatment, surrounding tissues were manually removed as much as possible. The nanofiber mats were repeatedly washed using milli-Q water and dehydrated using ethanol series. Finally, the dehydrated nanofiber mats were dried overnight using vacuum desiccator at room temperature.

In Vitro Degradation. Nanofiber mats with the size of 1×3 cm² were incubated in 5 mL of PBS with a pH of 7.27 for 4–12 weeks at 37 °C. The medium was changed every 2 weeks. After 4 and 12 weeks of incubation, the nanofiber mats were washed thoroughly with distilled water, vacuum-dried at room temperature, and then subjected to SEM observation.

Histological Observation. The surrounding tissues were excised together with the implanted nanofiber mats and fixed with 2.5% glutaraldehyde in PBS with a pH of 7. A small piece of the tissue was then embedded in paraffin before subjecting it to microtome sectioning. Hematoxylin and eosin (HE) were used for staining the tissues. The tissue response to nanofiber mats was evaluated from the coloration observed with a phase-contrast microscope.

Scanning Electron Microscopy (SEM). Nanofiber mat was placed on a stub and then coated with Au. The thickness of Au coat was about 15 nm. SEM images of nanofibers were obtained using a field emission scanning electron microscope (JSM-6330F, JEOL, Co. Ltd.) operating at an acceleration voltage of 5 kV and an emission current of 12 μA. For estimating the average diameter of nanofibers, diameter was measured at more than 60 points on the printed SEM image.

Wide-Angle X-ray Diffraction (WAXD). WAXD patterns of nanofiber mats were acquired under ambient condition using Rigaku RINT-2500 system operating at 40 kV and 200 mA. Measurements were performed on a Bragg–Brentano type $2\theta/\theta$ goniometer in a reflection mode. Ni-filtered Cu K α radiation ($\lambda = 0.15418$ nm) was collimated with a 1/2 deg divergence slit, 1/6 deg scatter slit and 0.15 mm receiving slit. Scans were performed three times in a 2θ range of 10–40° with a scan rate of 0.5°/min and 0.05° step.

Gel Permeation Chromatography (GPC) Analysis. The molecular weight analysis of the nanofiber mats was performed with gel-permeation chromatography at 40 °C, using a Shimadzu LC-10A GPC system equipped with a RID-10A refractive index detector and Shodex K-806 M and K-802 columns. Chloroform was used as the eluent at a flow rate of 0.8 mL min⁻¹. The calibration curve was prepared by using monodisperse polystyrene standards.

Results

Changes in the Appearance of Nanofiber Mats During Subcutaneous Implantation. Figure 1a,b shows SEM images of the PLLA and stereocomplexed PLA nanofibers, respectively. Both nanofibers possess similar morphology with the average fiber diameter of about 300 nm. However, totally different crystalline structure is formed in these nanofibers, as seen from the WAXD profiles in Figure 1c. PLLA nanofiber shows diffraction peaks at $2\theta = 15.1, 16.5$ (assigned to (110)/(200)), and 18.1° that are assigned to α -form homocrystal of PLA.¹² On the other hand, stereocomplexed PLA nanofiber showed diffraction peaks at $2\theta = 12.0$ (assigned to (110)), $20.8,$ and 24.1° that are assigned only to stereocomplex crystal of PLA.¹²




Figure 1. SEM images of (a) PLLA and (b) stereocomplexed PLA nanofibers and (c) wide-angle X-ray diffraction patterns of PLLA and stereocomplexed PLA nanofibers. Scale bars = 1 μm . PLLA nanofiber shows diffraction peaks at $2\theta = 15.1, 16.5$ (assigned to (110)/(200)), and 18.1° that are assigned to α -form homocrystal of PLA. On the other hand, stereocomplexed PLA nanofiber showed diffraction peaks at $2\theta = 12.0$ (assigned to (110)), 20.8 , and 24.1° that are assigned only to stereocomplex crystal of PLA.




Figure 2. Bulk appearances of the nanofiber mats of PLLA and stereocomplexed PLA (a) before implantation, (b) after 4 weeks of implantation and (c) after 12 weeks of implantation. Scale bars = 3 cm.

This shows that the stereocomplexed PLA nanofiber consists of only the stereocomplex crystal and does not contain homocrystal of PLLA and PDLA at all.

The bulk appearances of the nanofiber mats were observed before and after removing the surrounding tissues. Figure 2 shows the photographs of nanofiber mats before and after 4 week and 12 week implantations, respectively. Significant reduction in the size of the PLLA nanofiber mat was recognized with the increasing period of implantation. In particular, the PLLA nanofiber mat after a 12 week implantation was densely covered with the surrounding tissues and only small fragments of the nanofibers mat were recovered. On the other hand, the stereocomplexed PLA nanofiber mat showed a less degree of the reduction in size than the PLLA nanofiber mat. This suggests




Figure 3. Histological images of PLLA and stereocomplexed PLA nanofibers before and after 4 weeks of implantation. (a) PLLA, before implantation; (b) stereocomplexed PLA, before implantation; (c) PLLA, after implantation; (d) stereocomplexed PLA, after implantation. Tissues were stained with hematoxylineosin. Nuclei of the inflammatory cells are stained blue. The width of inflammatory cells is indicated by the arrows and lines in (a) and (b). Ellipsoid region in (a) and white arrows in (c) indicate the infiltration of surrounding tissues and fragmented nanofibers, respectively. ST: surrounding tissues; N: nanofiber mats. Scale bars = 50 μm .

that the in vivo degradation of the stereocomplexed PLA nanofiber mat occurs slower than the PLLA nanofiber mat.

Histological Observation of Nanofiber Mats with the Surrounding Tissues. Histological observations of the nanofiber mats were performed to investigate the degree of inflammatory reactions and penetration of the surrounding tissues into the nanofiber mats. Figure 3 shows the phase contrast images of ultrathin sections of the explanted nanofiber mats stained by hematoxylin-eosin. The nuclei of inflammatory cells were stained blue by the hematoxylin dye and their presence is an indication of tissue response toward the implanted nanofiber mats. As indicated by the arrows and lines in Figure 3a, a thick layer of inflammatory cells was accumulated at the interface between the PLLA nanofiber mat and the surrounding tissues. In contrast, the layer of accumulated inflammatory cells was thinner for the stereocomplexed PLA nanofiber mat, as shown in Figure 3b. This indicates that the stereocomplexed PLA nanofiber mat causes smaller degree of inflammatory reactions than the PLLA nanofiber mat.

Furthermore, delamination (indicated by the ellipsoid in Figure 3a) occurred on the surface of the PLLA nanofiber mat, and hence, the infiltration of the surrounding tissues was observed. However, no infiltration of the surrounding tissues was observed for the stereocomplexed PLA nanofiber mat. After 12 weeks of implantation, while the PLLA nanofiber mat was significantly fragmented (white arrows indicate the fragmented nanofiber mat), the stereocomplexed PLA nanofibers retained the mat-like bulk morphology. These trends are well correlated with the bulk appearances of the nanofiber mats and support the observation that the in vivo degradation of the stereocomplexed PLA nanofiber mat proceeds slower than the PLLA nanofiber mat.

SEM Observation. SEM observation was performed for the nanofiber mats before and after 4 weeks and 12 weeks of implantation. Figure 4 shows the SEM images of nanofiber mats before implantation, after implantation and incubation at different periods of time. As for PLLA, cleavage of each strand of nanofiber occurred after 4 weeks. Furthermore, after 12 weeks, a decrease in the density of the nanofiber mat was observed. This is consistent with the histological image showing the fragmentation of the PLLA nanofiber mat. On the other hand, no cleavage of the stereocomplexed PLA nanofibers was observed even after 12 weeks of implantation.




Figure 4. SEM images of PLLA (left) and stereocomplexed PLA (right) nanofibers. Upper row, before implantation; middle row, after 4 weeks of implantation; lower row, after 12 weeks of implantation. The surrounding tissues were removed by trypsin treatment. Scale bars = 1 μm .




Figure 5. Wide-angle X-ray diffraction patterns of PLLA and stereocomplexed nanofibers before and after 4 weeks of implantation. PLLA nanofiber showed diffraction peaks at $2\theta = 15.1^\circ$, 16.5° , and 18.1° that are assigned to homopolymer crystal of PLLA. On the other hand, stereocomplexed PLA nanofiber showed diffraction peaks at $2\theta = 12.0^\circ$, 20.8° , and 24.1° that are assigned to stereocomplexed crystal. No diffraction peaks assigned to homopolymer crystal were observed in stereocomplexed PLA nanofiber.

Changes in Crystallinity. Figure 5 shows the WAXD patterns of the PLLA and stereocomplexed PLA nanofibers before and after 4 weeks of implantation. While the PLLA nanofiber showed diffractions that are assigned to the α -form




Figure 6. GPC elution profiles of (a) PLLA and (b) stereocomplexed PLA nanofibers before and after implantation in vivo for 4 weeks and 12 weeks and before and after in vitro degradation for 4 weeks and 12 weeks.

crystal of PLA, the stereocomplexed PLA nanofiber showed diffractions assigned only to stereocomplexed crystal.¹² The crystallinity of both nanofibers was calculated as the ratio between the integrals of crystalline diffraction intensity and the total diffraction intensity. While the PLLA nanofiber showed considerable decrease in its crystallinity from 86 to 58%, the stereocomplexed PLA nanofiber showed a smaller decrease from 61 to 49%. These results show that the crystallinity of the stereocomplexed PLA is not so much lowered by implantation, while that of PLLA nanofiber significantly decreases. These results support the higher stability of stereocomplexed PLA nanofiber than PLLA nanofiber, as seen from visual inspection of the explanted nanofiber mat and the histological observation.

GPC Analysis. The possibility of the cleavage of molecular chains during implantation, as suggested from SEM and WAXD data, was investigated by GPC analysis. The GPC elution profiles are shown in Figure 6. Table 1 shows the number-averaged molecular weight, M_n , and the polydispersity index, M_w/M_n , of the PLLA and stereocomplexed PLA nanofibers before and after 4 weeks of implantation. Data for original PLLA are also shown in Table 1. In the case of 12 weeks, GPC data of stereocomplexed PLA were not obtained because of its low solubility in chloroform. PLLA nanofiber showed a decrease in M_n during the implantation. In contrast, the M_n of stereocomplexed PLA nanofiber remained unchanged despite the decrease in M_w/M_n for 4 weeks of implantation. These results indicate that stereocomplexed PLA was not degraded during implantation, while the PLLA chains in the nanofiber were considerably degraded. Additionally, in the case of the stereocomplexed PLA nanofiber, the extraction of low molecular weight fraction might occur during implantation.

In Vitro Degradation. To consider the results obtained from the in vivo experiment in terms of biocompatibility and bioabsorption, changes in the structure and properties of the nanofibers after in vitro incubation were investigated. As seen in Figure 7, both PLLA and stereocomplexed PLA nanofibers

Table 1. Number-Averaged Molecular Weight (M_n) and Polydispersity Index (M_w/M_n) of Original PLLA and PLA Nanofibers^a

| | PLLA | | PDLA | | stereocomplexed PLA | |
|--------------------------------|-------------------|-----------|-------------------|-----------|---------------------|--------------|
| | M_n | M_w/M_n | M_n | M_w/M_n | M_n | M_w/M_n |
| original | 4.7×10^5 | 1.8 | 2.2×10^5 | 1.5 | | |
| nanofiber before implantation | 3.8×10^5 | 2.3 | | | 8.7×10^4 | 3.3 |
| after 4 weeks of implantation | 3.0×10^5 | 2.4 | | | 8.6×10^4 | 2.3 |
| after 12 weeks of implantation | 1.7×10^5 | 2.3 | | | ^b | ^b |

^a PLLA and stereocomplexed PLA before and after 4 weeks and 12 weeks of implantation. ^b Not obtained due to the poor solubility in chloroform.




Figure 7. SEM images of PLLA (left) and stereocomplexed PLA (right) nanofibers after 4 weeks (upper) and 12 weeks (lower) in vitro degradation in PBS. Scale bars = 1 μ m.

after in vitro incubation showed a considerable increase in the fiber diameter. This suggests that the significant swelling of the nanofibers occurred during the incubation. Interestingly, the stereocomplexed PLA nanofiber showed a smaller degree of swelling (from 300 to 600 nm) than the PLLA nanofiber (from 300 to 1200 nm). Because strong interaction works between molecular chains of PLLA and PDLA in the stereocomplexed PLA nanofiber, the swelling of the stereocomplexed PLA nanofiber might be suppressed.

GPC data of the nanofibers before and after in vitro degradation were also obtained, as shown in Figure 6b. The M_n and M_w/M_n estimated from the GPC curves are listed in Table 2. The M_n of stereocomplexed PLA was almost unchanged while that of PLLA showed a decrease from 3.8×10^5 to 1.8×10^5 . These trends are consistent with the molecular weight data before and after the implantation in vivo as shown in Table 1.

The difference in the swelling behavior and molecular weight change in vitro between the stereocomplexed PLA and PLLA nanofibers may explain the results of the subcutaneous implantation in vivo in which the stereocomplexed PLA nanofiber showed smaller degree of absorption than the PLLA nanofiber.

Discussion

Degradation Mechanism of PLLA and Stereocomplexed PLA Nanofibers In Vivo. A schematic representation of the degradation mechanism of the PLLA and stereocomplexed PLA nanofibers is shown in Figure 8. For the PLLA nanofiber, it is believed that the molecular chains in the amorphous region between lamella crystals are preferentially hydrolyzed due to the intracrystalline swelling. This leads to the cleavage of a nanofiber and a decrease in the molecular weight. Then the chain-end degradation at the edge of the cleaved nanofiber may occur and lead to the decrease in the crystallinity. The cleavage of nanofiber may facilitate the delamination and the subsequent fragmentation of the nanofiber mats and, consequently, the




Figure 8. Schematic representation of the structural changes of (a) PLLA nanofiber and (b) stereocomplexed PLA nanofiber during implantation in vivo. For PLLA nanofiber, the amorphous chains between lamella crystals are preferentially hydrolyzed, leading to the cleavage of the nanofiber. Then, the chain-end degradation occurs at the edge of the cleaved nanofiber. Crystallinity of the PLLA nanofiber is thus considerably lowered. In contrast, degradation of stereocomplexed PLA is suppressed by the strong interaction between PLLA and PDLA chains, although the crystallinity slightly decreases.

Table 2. Number-Averaged Molecular Weight (M_n) and Polydispersity Index (M_w/M_n) of PLLA and Stereocomplexed PLA Nanofibers^a

| | PLLA | | stereocomplexed PLA | |
|-------------------------------|-------------------|-----------|---------------------|-----------|
| | M_n | M_w/M_n | M_n | M_w/M_n |
| before degradation | 3.8×10^5 | 2.3 | 8.7×10^4 | 3.3 |
| after 4 weeks of degradation | 1.4×10^5 | 3.5 | 8.4×10^4 | 3.0 |
| after 12 weeks of degradation | 1.8×10^5 | 3.0 | 6.9×10^4 | 2.2 |

^a Before and after 4 weeks and 12 weeks of degradation in vitro.

infiltration of surrounding tissues in the PLLA nanofiber mat. Inflammatory reaction at the early stage may be due to the acidic low-molecular-weight degradation products and fragmented nanofibers.

A different situation was observed for the stereocomplexed PLA nanofibers. It is supposed that a single stereocomplexed PLA nanofiber is composed of PLLA and PDLA chains aligned

in a side-by-side manner. Accordingly, it is well-known that molecular interaction between PLLA and PDLA chains is strong, leading to higher melting temperature. Such molecular arrangement may suppress the hydrolysis of molecular chains in vivo. Thus, the stereocomplexed nanofiber morphology is retained. As a result, inflammatory reaction is limited at the vicinity of the interfacial region between nanofiber mats and the surrounding tissues.

General Discussion. Physiological response of tissues against implanted foreign materials is one of the most significant subjects to be considered in the development of medical biomaterials. In the case of polymeric biomaterials, the degree of the tissue responses, such as inflammatory reactions, partly depends on the chemical structure and, as a consequence, surface hydrophilic nature of the polymers.²³ Additionally, for biodegradable polymers, the degree of tissue responses is affected by the degradability in vivo.²⁴ For example, poly(glycolic acid) that undergoes degradation in vivo generally in 2–4 weeks is known to cause acute inflammatory reaction as the degradation proceeds.²⁵ It is known that the hydrolysis by body fluids is the major mechanism contributing in vivo degradation of polymeric biomaterials. We have already shown that the degradation behavior of poly(hydroxyalkanoate)s (PHAs) in vivo are largely affected by the monomer composition.²⁶ Nanofiber scaffolds made from these PHAs, ranging from poly[(*R*)-3-hydroxybutyrate] to poly[(*R*)-3-hydroxybutyrate-co-97 mol % 4-hydroxybutyrate] lead to contrasted tissue responses. The tissue responses were well correlated with the degradability of each polymer scaffolds. The present study using nanofibers of PLLA and stereocomplexed PLA suggested the correlation between the degree of inflammatory reaction in vivo and the change in the bulk size of each nanofiber mats. The changes in bulk size of the nanofibers were correlated to the changes in the microscopic morphology, crystallinity, and molecular weight. All these factors give evidence that the stereocomplexed PLA nanofibers are more stable and thus provoke lower degree of inflammation in vivo than the PLLA nanofibers.

In general, inflammatory reaction is favored in the case where healing occurs in a short period of time. For example, inflammatory reaction stimulates and accelerates the regeneration of some kinds of epithelial tissues. On the other hand, in the case where healing requires a longer time, chronic inflammatory response is not favored. For example, suppression of the inflammatory responses against artificial vessel has significance for treatment of the circulatory organs that requires a period of more than half a year. From this viewpoint, our results show that the stereocomplexed PLA nanofibers are suitable for the purposes where the chronic inflammatory reaction should be avoided, for example, guided nerve regeneration or blood vessel augmentation. On the other hand, conventional PLLA nanofibers may be suitable for the rapidly bioresorbable materials, for example, wound healing patches. Such versatility of the biodegradability would expand the potential of PLAs as biomaterials.

Conclusion

Fiber morphology, crystallinity, and molecular weight of PLLA and stereocomplexed PLA nanofibers before and after

implantation in vivo were investigated using SEM, WAXD, and GPC. The stereocomplexed PLA nanofiber retained its fiber morphology, crystallinity, and molecular weight after a 12 week implantation. On the other hand, the PLLA nanofiber showed breakdown of the fiber morphology and significant decrease in crystallinity and molecular weight. The degree of inflammatory reaction against the nanofibers in vivo was correlated to the degradation behavior. The larger stability against hydrolysis of stereocomplexed PLA nanofiber, attributed to the strong interaction between PLLA and PDLA chains in the nanofiber, was confirmed by in vitro degradation.

Acknowledgment. This work has been supported by a grant provided for Ecomolecular Research II in RIKEN Institute (The Institute of Physical and Chemical Research), Japan, and by a Grant-in-Aid from the Ministry of Education, Culture, Sports, Science and Technology, Japan (No. 19350075, to T.I.). We thank Ms. Noreen Fundador for the English correction of our manuscript.

References and Notes

- (1) Langer, R.; Vacanti, J. P. *Science* **1993**, *260*, 920–926.
- (2) Reneker, D. H.; Chun, I. *Nanotechnology* **1996**, *7*, 216–223.
- (3) Morota, K.; Matsumoto, K.; Mizukoshi, T.; Konosu, Y.; Minagawa, M.; Tanioka, A.; Yamagata, Y.; Inoue, K. *J. Colloid Interface Sci.* **2004**, *279*, 484–492.
- (4) Murugan, R.; Ramakrishna, S. *Tissue Eng.* **2006**, *12*, 435–447.
- (5) Buchko, C. J.; Chen, L. C.; Shen, Y.; Martin, D. C. *Polymer* **1999**, *40*, 7397–7407.
- (6) Zong, X.; Kim, K.; Fang, D.; Ran, S.; Hsiao, B. S.; Chu, B. *Polymer* **2002**, *43*, 4403–4412.
- (7) Zong, X.; Ran, S.; Kim, K.-S.; Fang, D.; Hsiao, B.; Chu, B. *Biomacromolecules* **2003**, *4*, 416–423.
- (8) Ikada, Y.; Tsuji, H. *Macromol. Rapid Commun.* **2000**, *21*, 117–132.
- (9) Iwata, T.; Doi, Y. *Sen'i Gakkaishi* **2001**, *57*, 172–177.
- (10) Ikada, Y.; Jamshidi, K.; Tsuji, H.; Hyon, S. H. *Macromolecules* **1987**, *20*, 904–906.
- (11) Tsuji, H. *Macromol. Biosci.* **2005**, *5*, 569–597.
- (12) Okihara, T.; Tsuji, M.; Kawaguchi, A.; Katayama, K.; Tsuji, H.; Hyon, S. H.; Ikada, Y. *J. Macromol. Sci., Part B: Phys.* **1991**, *30*, 119–140.
- (13) Tsuji, H. *Polymer* **2000**, *41*, 3621–3630.
- (14) Tsuji, H.; Suzuki, M. *Sen'i Gakkaishi* **2001**, *57*, 198–202.
- (15) Tsuji, H.; Miyauchi, S. *Biomacromolecules* **2001**, *2*, 597–604.
- (16) Takasaki, M.; Ito, H.; Kikutani, T. *J. Macromol. Sci., Part B: Phys.* **2003**, *42*, 57–73.
- (17) Furuhashi, Y.; Kimura, Y.; Yamane, H. *J. Polym. Sci., Part B: Polym. Phys.* **2007**, *45*, 218–228.
- (18) Tsuji, H.; Nakano, M.; Hashimoto, M.; Takashima, K.; Katsura, S.; Mizuno, A. *Biomacromolecules* **2006**, *7*, 3316–3320.
- (19) Ishii, D.; Lee, W.-K.; Kasuya, K.-I.; Iwata, T. *J. Biotechnol.* **2007**, *132*, 318–324.
- (20) Kim, K.; Yu, M.; Zong, X.; Chiu, J.; Fang, D.; Seo, Y.-S.; Hsiao, B. S.; Chu, B.; Hadjiargyrou, M. *Biomaterials* **2003**, *24*, 4977–4985.
- (21) Zeng, J.; Chen, X.; Liang, Q.; Xu, X.; Jing, X. *Macromol. Biosci.* **2004**, *4*, 1118–1125.
- (22) You, Y.; Min, B.-M.; Lee, S. J.; Lee, T. S.; Park, W. H. *J. Appl. Polym. Sci.* **2005**, *95*, 193–200.
- (23) Wang, Y.-X.; Robertson, J. L.; Spillman, W. B.; Claus, R. O. *Pharm. Res.* **2004**, *21*, 1362–1373.
- (24) Hasirci, V.; Lewandrowski, K.; Gresser, J. D.; Wise, D. L.; Trantolo, D. J. *J. Biotechnol.* **2001**, *86*, 135–150.
- (25) Ceonzo, K.; Gaynor, A.; Shaffer, L.; Kojima, K.; Vacanti, C. A.; Stahl, G. A. *Tissue Eng.* **2006**, *12*, 301–308.
- (26) Tan, H. Y.; Ishii, D.; Mahara, A.; Murakami, S.; Yamaoka, T.; Sudesh, K.; Samian, R.; Fujita, M.; Maeda, M.; Iwata, T. *Biomaterials* **2008**, *29*, 1307–1317.

BM8009363

Modification of PLA Scaffolds Using Bioactive Peptide-Oligo (Lactic Acid) Conjugates

Sachiro Kakinoki^{1,2}, Sho Uchida^{1,3}, Tomo Ehashi^{1,2}, Akira Murakami³, and Tetsuji Yamaoka^{1,2}

¹Department of Biomedical Engineering, National Cardiovascular Center Research Institute, 5-7-1 Fujishirodai, Suita, Osaka 565-8565, Japan, ²JST, CREST, 5 Sanbancho, Chiyoda-ku, Tokyo 102-0075, Japan, ³Department of Polymer Science and Engineering, Kyoto Institute of Technology, Kyoto 606-8585, Japan.
e-mail: yamtet@ri.ncvc.go.jp

A novel method for surface modification of PLA scaffold based on amphiphilic conjugates composed of oligo lactic acid (OLA) and bioactive peptide was designed and developed. PLA thin-films modified with the amphiphilic OLA-AG73 conjugates were prepared by spin-coating. Cell adhesion and neurite outgrowth of PC12 cells on the modified thin-films were greatly improved.

Keywords: AG73, nerve regeneration, PLA, scaffolds, surface modification


Introduction

Tissue engineering has been proposed as an approach to create tissues and organs by use of various scaffolds as a temporary extra-cellular matrix. Poly (lactic acid) (PLA) is a preferred biodegradable material since it is non-enzymatically hydrolyzed to low-toxic lactic acid *in vivo* and has high mechanical properties and excellent shaping and molding properties.

On the other hand, PLA has no specific bioactivities and then is preferred to be modified with bioactive molecules. A variety of bioactive peptides has been reported to be useful for tissue regeneration so far. For example, RGD sequence isolated from fibronectin is well known to support cell adhesion. Various modification techniques for PLA which has no functional groups have been proposed [1] but they are quite hard to apply to the nano-structured PLA scaffold since they are very fragile. In this report, we developed amphiphilic conjugates composed of bioactive peptides and oligo (lactic acid) (OLA) to functionalize nano-structured PLA scaffolds and evaluate their bioactivities.

Results and Discussion

Bioactive sequence, RKRLQVQLSIRT (AG73) [2], which has been reported to accelerate the neurite outgrowth *in vitro* was selected. OLA whose hydroxyl group end is capped with acetyl group was synthesized by condensation reaction. The OLA-AG73 conjugates were synthesized by Fmoc solid phase procedure (Scheme 1).



Scheme 1. Synthesis of Ac-OLA26-AG73.




Figure 1. Neurite outgrowth of PC12 cells on PLA (A) and PLA/OLA-AG73 (B) thin-films.

Three weight % of OLA-AG73 conjugates were added to 10 weight % of PLA solution in hexafluoro isopropanol, and the mixed solutions were spin coated onto cover glass (φ 14 mm) or electro spun to aluminum foil, resulting in surface modified thin-films and nano-fiber sheets respectively. As is shown in Figure 1, the cell adhesion and neurite outgrowth of PC12 cells on PLA/OLA-AG73 thin-film were improved and reached to longitudinal and transversal respectively. These behaviors must be resulted from AG73 peptides immobilized on thin-film surface but other factors may also affect it. The physicochemical characteristics should be changed even when only 3 % of OLA-AG73 was added. In addition, the surface density of OLA-AG73 on thin-film and its releasing profiles should be analyzed in detail.

In general nano-structured PLA scaffolds are much more difficult to be modified than the bulk materials because they are very weak and fragile against to mechanical stress, chemical reaction, and thermal treatment. The newly developed OLA-Peptide conjugates were found to be very powerful tool for modifying such ultra thin-films or nano-fibers just by adding only 3 % to the dope before processing.

References

1. Fujiwara T., Mukose T., Yamaoka, T., Yamane H., Sakurai S., Kimura Y. (2001) *Macromol. Biosci.*, **1**, 204-208.
2. Weeks B. S., Nomizu M., Ramachandran R.S., Yamada Y., Kleinman H. K. (1998) *Exp. Cell Res.*, **243**, 375-382.

**Oppression of Left Main Trunk Due to Pseudoaneurysm With Graft Detachment
in Patients With Behcet Disease Previously Treated by Bentall Procedure**

Yu Kataoka, Takeshi Tsutsumi, Kouhei Ishibashi, Masahiro Higashi, Isao Morii,
Atsushi Kawamura, Hatsue Ishibashi-Ueda, Kenji Minatoya, Hitoshi Ogino and
Yoritaka Otsuka

Circulation 2009;119:2858-2859

DOI: 10.1161/CIRCULATIONAHA.108.803387

Circulation is published by the American Heart Association, 7272 Greenville Avenue, Dallas, TX
72514

Copyright © 2009 American Heart Association. All rights reserved. Print ISSN: 0009-7322. Online
ISSN: 1524-4539

The online version of this article, along with updated information and services, is
located on the World Wide Web at:

<http://circ.ahajournals.org/cgi/content/full/119/21/2858>

Data Supplement (unedited) at:

<http://circ.ahajournals.org/cgi/content/full/119/21/2858/DC1>

Subscriptions: Information about subscribing to Circulation is online at
<http://circ.ahajournals.org/subscriptions/>

Permissions: Permissions & Rights Desk, Lippincott Williams & Wilkins, a division of Wolters
Kluwer Health, 351 West Camden Street, Baltimore, MD 21202-2436. Phone: 410-528-4050. Fax:
410-528-8550. E-mail:
journalpermissions@lww.com

Reprints: Information about reprints can be found online at
<http://www.lww.com/reprints>

Oppression of Left Main Trunk Due to Pseudoaneurysm With Graft Detachment in Patients With Behcet Disease Previously Treated by Bentall Procedure

Yu Kataoka, MD; Takeshi Tsutsumi, MD; Kouhei Ishibashi, MD; Masahiro Higashi, MD; Isao Morii, MD; Atsushi Kawamura, MD; Hatsue Ishibashi-Ueda, MD; Kenji Minatoya, MD; Hitoshi Ogino, MD; Yoritaka Otsuka, MD

A 35-year-old Japanese man was admitted to our hospital because of congestive heart failure in January 2006. Echocardiography showed severe aortic regurgitation and partial ruptured aneurysm of the Valsalva sinus. Because he had already presented oral aphthae, uveitis, skin lesions with bouton, and genital ulceration, this case was diagnosed as a complete form of Behcet disease and the Bentall operation was performed. He was discharged without any complications. However, he experienced chest pain with ST-segment

depression 3 months after the Bentall operation although no significant stenosis could be seen by preoperative coronary angiography in January 2006. This patient had III/VI systolic murmur of intensity of Levine on the third left sternal border. Transthoracic and transesophageal echocardiography revealed the echo-free space around the aortic graft and an abnormal jet from the left ventricular outflow to that echo-free space (online-only Data Supplement Movies I and II). Multislice computed tomography showed the development of




Figure 1. A, Multislice computed tomography reveals the development of multiple pseudoaneurysms around the aortic graft (arrows). B, One of those pseudoaneurysms oppresses the left main trunk (triangle) and causes severe stenosis (arrows).

From the Division of Cardiology (Y.K., T.T., K.I., Y.O.), Cardiovascular Surgery (K.M., H.O.), Radiology (M.H.), and Pathology (H.I.), National Cardiovascular Center, Osaka, Japan; Division of Cardiology, Hokusetsu General Hospital, Takatsuki, Japan (I.M.); and Division of Cardiology, Central Hospital, Hiroshima, Japan (A.K.).

The online-only Data Supplement is available with this article at <http://circ.ahajournals.org/cgi/content/full/119/21/2528/DC1>.

Address for correspondence: (current address), Yu Kataoka, MD, Division of Cardiology, Department of Medicine, National Cardiovascular Center, 5-7-1 Fujishiro-dai, Suita, Osaka 565-8565, Japan. Tel:81-6-6833-5012, Fax:81-6-6872-7486, Email: kataoka@hsp.nccvc.go.jp
(*Circulation*. 2009;119:2858-2859.)

© 2009 American Heart Association, Inc.

Circulation is available at <http://circ.ahajournals.org>

DOI: 10.1161/CIRCULATIONAHA.108.803387




Figure 2. ECG demonstrates the presence of severe ischemic change on day 5 after admission.

multiple pseudoaneurysms around the aortic graft, which oppressed the left main trunk and caused severe stenosis of the left main trunk (Figure 1A and 1B). Because he had progressive angina with severe ST-segment changes (Figure 2), the Bentall operation was reperformed on an urgent basis, in addition to coronary artery bypass grafting. The aortic graft was detached at the right coronary cusp and multiple pseudoaneurysms were seen at the right and left coronary cusps. In addition, a pseudoaneurysm at the left coronary cusp oppressed the left main trunk, and severe stenosis in the left main trunk was observed. After the previously implanted composite graft was resected, new composite graft was implanted into the annulus. The left coronary ostia was

reimplanted using the button technique, and coronary artery bypass grafting was performed for the right coronary artery. Histological examination of the explanted synthetic graft of the aortic root revealed poor organization with severe inflammatory cell infiltration such as neutrophils and macrophages (Figure 3). Numerous Gram-positive cocci were also recognized in the graft (Figure 3).

Graft detachment or pseudoaneurysm after the Bentall operation in Behcet disease occurs in 20% to 40% of cases.^{1,2} However, there are no case reports like the present case. In this case, the inflammation level was not satisfactorily controlled and the C-reactive protein level on admission was high (9.6 mg/dL). Therefore, inflammation leading to fragility of the aortic wall seems to cause these rare complications. After reoperation and strict control of inflammation using methylprednisolone, the patient had no recurrence of pseudoaneurysm formation during a 2-year follow-up period.

Acknowledgments

We would like to thank Mrs Hiromi Maeda for her excellent secretarial assistance, and the nurses and residents in the coronary care unit of the National Cardiovascular Center for their cooperation.

Disclosures

None.

References

1. Ando M, Kosakai Y, Okita Y, Nakano K, Kitamura S. Surgical treatment of Behcet's disease involving aortic regurgitation. *Ann Thorac Surg.* 1999;68:2136–2140.
2. Alpagut U, Ugurlucan M, Dayioglu E. Major arterial involvement and review of Behcet's disease. *Ann Vasc Surg.* 2007;21:232–239.




Figure 3. Histological examination of the explanted synthetic graft of the aortic root reveals poor organization with severe inflammatory cell infiltration such as neutrophils and macrophages (left, arrows). Numerous Gram-positive cocci were also recognized in the graft (right).